

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 8374 Dr. Umbreen

#### To: (Khalid Bashir) Ittefaq Building Solution Pvt. Ltd.

Project: Piling Works at Shadman 98 Kamran Steel.

Our Ref. No. CL/CED/	7818	Dated:	15-04-19
Your Ref. No.	IBS/KMS/CS01	Dated:	27-03-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

02-04-19 Tested on:

12-

12-04-19 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	19	3	2019	6Diax12	14	28.28	57	4520	Non Engraved
2	4000 Psi	19	3	2019	6Diax12	14	28.28	61	4840	Non Engraved
END										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### (Khalid Bashir) To: Ittefaq Building Solution Pvt. Ltd.

Project: Columns at Ghani Farms, Sahianwala.

Our Ref. No. CL/CED/ 7819 Dated: 15-04-19 Dated: Your Ref No IBS/LCH/CB01 01-04-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

02-04-19 Tested on:

12-04-19 in dry/wet condition

8376

Dr. Umbreen

			otina	Data*	Sizo	Woight	Area of	Ultimata	Liltimata	
ö		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	3000 Psi	27	1	2019	6Diax12	13.2	28.28	31	2460	Non Engraved
2	3000 Psi	2	2	2019	6Diax12	13	28.28	35	2780	Non Engraved
END										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (QCD)

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7820	Dated:	15-04-19
Your Ref. No.	QCD/280-81	Dated:	02-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19 Tested on:

11-04-19 in dry/wet condition

Ir						[	[	1		1
		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1		30	1	2019	6x6x6	8.6	36	77	4800	Engraved
2		30	1	2019	6x6x6	8	36	88	5480	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (QCD)

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7821	Dated:	15-04-19
Your Ref. No.	QCD/286-87	Dated:	02-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19 Tested on:

11-04-19 in dry/wet condition

<b></b>										
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1		29	1	2019	6x6x6	8.2	36	73	4550	Engraved
2		29	1	2019	6x6x6	8.4	36	77	4800	Engraved
3		30	1	2019	6x6x6	8.2	36	59	3680	Engraved
4		30	1	2019	6x6x6	8.2	36	80	4980	Engraved
5		31	1	2019	6x6x6	8.6	36	69	4300	Engraved
6		31	1	2019	6x6x6	8.4	36	54	3360	Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

#### **Director/Dy. Director Concrete Laboratory**



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8386

Dr. Aqsa

To: Deputy Director (QCD)

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

 Our Ref. No. CL/CED/
 7822
 Dated:
 15-04-19

 Your Ref. No.
 QCD/288-89
 Dated:
 02-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19 Tested on:

11-04-19 in dry/wet condition

		Са	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(grr	ıs)			(Sq. in)	(Tons/lbs)	(Psi)		
1		2	2	2019	6x6x6	8.2	36	58	3610	Engraved
2		2	2	2019	6x6x6	8	36	69	4300	Engraved
3		4	2	2019	6x6x6	8.2	36	71	4420	Engraved
4		4	2	2019	6x6x6	8.2	36	90	5600	Engraved
5		5	2	2019	6x6x6	8.2	36	59	3680	Engraved
6		5	2	2019	6x6x6	8	36	56	3490	Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (QCD)

8386 Dr. Aqsa

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7823	Dated:	15-04-19
Your Ref. No.	QCD/290-91	Dated:	02-04-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19 Tested on:

11-04-19 in dry/wet condition

Ir		1				1	1	I		
		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	Vet W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		6	2	2019	6x6x6	8.2	36	77	4800	Engraved
2		6	2	2019	6x6x6	8	36	45	2800	Engraved
3		8	2	2019	6x6x6	8.2	36	66	4110	Engraved
4		8	2	2019	6x6x6	8.2	36	65	4050	Engraved
5		9	2	2019	6x6x6	8.2	36	52	3240	Engraved
6		9	2	2019	6x6x6	8.6	36	104	6480	Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### **Deputy Director (QCD)** To:

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7824	Dated:	<b>15</b> -04-19
Your Ref. No.	QCD/292-93	Dated:	<b>02</b> -04-19

Tested on:

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

° Z

ທັ

1

2

3

4

5

6

8

9

10

11

12

13

14

15

16

03-04-19

11-04-19 in dry/wet condition

Casting Date\* Size Weight Area of Ultimate Ultimate X-Mark\* /Wet Weight (in) (lbs./gms) load Stress Remarks Section (gms) (Tons/lbs) (Sq. in) (Psi) 12 2 2019 6x6x6 8.4 36 59 3680 Engraved 2 2019 6x6x6 12 8 50 3120 Engraved 36 13 2 2019 6x6x6 8.6 36 64 3990 Engraved 2 13 2019 6x6x6 8.4 36 58 3610 Engraved 2 14 2019 6x6x6 8 70 4360 Engraved 36 14 2 2019 6x6x6 8 3610 36 58 Engraved End ---

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

#### **Director/Dy. Director Concrete Laboratory**



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Deputy Director (QCD)

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7825-1 of 2	Dated:	<b>15</b> -04-19
Your Ref. No.	QCD/284-85	Dated:	<b>02</b> -04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-**04**-19

Tested on: 11-

11-04-19 in dry/wet condition

8386

Dr. Aqsa

			e	<b>D</b> / +	<u>e</u> :		• •		1.110	
	Mark*	Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		21	2	2019	6x6x6	8.2	36	48	2990	Engraved
2		21	2	2019	6x6x6	8	36	59	3680	Engraved
3		22	2	2019	6x6x6	8.2	36	61	3800	Engraved
4		22	2	2019	6x6x6	8	36	56	3490	Engraved
5		23	2	2019	6x6x6	8.2	36	89	5540	Engraved
6		23	2	2019	6x6x6	8	36	61	3800	Engraved
7		25	2	2019	6x6x6	8	36	66	4110	Engraved
8		25	2	2019	6x6x6	8.2	36	44	2740	Engraved
9		28	2	2019	6x6x6	8.8	36	73	4550	Engraved
10		28	2	2019	6x6x6	8.2	36	57	3550	Engraved
11		1	3	2019	6x6x6	8	36	70	4360	Engraved
12		1	3	2019	6x6x6	8.4	36	47	2930	Engraved
13		2	3	2019	6x6x6	8.2	36	75	4670	Engraved
14		2	3	2019	6x6x6	8	36	79	4920	Engraved
End										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### **Deputy Director (QCD)** To:

WASA LDA, Lahore.

Project:Tend. # P&S/25.01/6016-Manufac.of RCC Manhole Covers in Diff.Sizes.(M/s Eagle Pipe Indus. Pack-

Our Ref. No. CL/CED/	7825-2 of 2	Dated:	15-04-19
Your Ref. No.	QCD/284-85	Dated:	02-04-19

Tested on:

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19

11-04-19 in dry/wet condition

8386

Dr. Aqsa

1		T								
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(grr	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		5	3	2019	6x6x6	8	36	75	4670	Engraved
2		5	3	2019	6x6x6	8.6	36	68	4240	Engraved
3		6	3	2019	6x6x6	8	36	60	3740	Engraved
4		6	3	2019	6x6x6	8.4	36	49	3050	Engraved
End										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: M Rizwan Shoukat, Project Manager GINUM Gujranwala. Pakistan Atomic Energy Commission.

Project: Mumty Slab & Water Tank Walls.

Our Ref. No. CL/CED/	7826	Dated:	15-04-19
Your Ref. No.	Nil	Dated:	02-04-19

Tested on:

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-04-19

11-04-19 in dry/wet condition

		1								
		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	Vet W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		26	3	2019	6x6x6	8.4	36	56	3490	Non Engraved
2		26	3	2019	6x6x6	8.2	36	90	5600	Non Engraved
3		26	3	2019	6x6x6	8.4	36	83	5170	Non Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

#### **Director/Dy. Director Concrete Laboratory**



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Saqib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Our Ref. No. CL/CED/	7827	Dated:	15-04-19
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-04-19 Tested on:

12-04-19 in dry/wet condition

Casting Date\* Size Weight Area of Ultimate Ultimate o Z X-Mark\* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ທັ (Tons/lbs) (gms) (Sq. in) (Psi) 1 4000 Psi, Col. 1 3 2019 6Diax12 13.2 28.28 92 7290 Engraved 2 1 3 2019 6Diax12 28.28 4000 Psi, Col. 13.2 94 7450 Engraved 3 4000 Psi, Col. 1 3 2019 6Diax12 13.2 28.28 94 7450 Engraved End ---\_\_\_ \_\_\_ \_\_\_\_ 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Sagib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Our Ref. No. CL/CED/	7828	Dated:	15-04-19
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-**04**-19 Tested on:

12-04-19 in dry/wet condition

		<u> </u>								
		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	3000 Psi, Slab	21	3	2019	6Diax12	13.2	28.28	63	5000	Engraved
2	3000 Psi, Slab	21	3	2019	6Diax12	13.4	28.28	73	5790	Engraved
3	3000 Psi, Slab	21	3	2019	6Diax12	13.2	28.28	55	4360	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Sagib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Our Ref. No. CL/CED/	7829	Dated:	15-04-19
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-**04**-19 Tested on:

12-04-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight		Size (in)	Weight (lbs./gms)	Area of X-	Ultimate	Ultimate Stress	Remarks	
Sr.			(gm	-	()	(1201) gillo)	Section (Sq. in)	(Tons/lbs)	(Psi)	rtomanto
1	3000 Psi, Slab	13	3	2019	6Diax12	13.2	28.28	81	6420	Engraved
2	3000 Psi, Slab	13	3	2019	6Diax12	13.2	28.28	71	5630	Engraved
3	3000 Psi, Slab	13	3	2019	6Diax12	13.2	28.28	81	6420	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Saqib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Our Ref. No. CL/CED/	7830	Dated:	15-04-19
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-**04**-19 Tested on:

12-04-19 in dry/wet condition

ö	Mark*	Casting Date* /Wet Weight (gms)			Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,							(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi, Col.	28	2	2019	6Diax12	13.4	28.28	81	6420	Engraved
2	4000 Psi, Col.	28	2	2019	6Diax12	13.2	28.28	75	5950	Engraved
3	4000 Psi, Col.	28	2	2019	6Diax12	13	28.28	79	6260	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Saqib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Our Ref. No. CL/CED/	7831	Dated:	15-04-19	
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19	

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-04-19 Tested on:

12-04-19 in dry/wet condition

I						1				
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi, Col.	26	2	2019	6Diax12	13.2	28.28	84	6660	Engraved
2	4000 Psi, Col.	26	2	2019	6Diax12	13	28.28	94	7450	Engraved
3	4000 Psi, Col.	26	2	2019	6Diax12	13.8	28.28	104	8240	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Abdul Rauf Saqib, Project Manager

8394 Dr. Umbreen

Ittefaq Construction Services, 32-R, Shah Alam Road, Johar Town, Lahore. Project: Construction of Apartments Building, Plot # 81, Block-C/1, Gulberg III, Lahore.

Tested on:

Our Ref. No. CL/CED/	7832	Dated:	15-04-19
Your Ref. No.	ICS/M.A/0	Dated:	04-04-19

#### COMPRESSION TEST REPORT

#### Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-04-19

12-04-19 in dry/wet condition

·		1			[	1	I	1		
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi, Col.	22	2	2019	6Diax12	13.8	28.28	96	7610	Engraved
2	4000Psi, Share W.	22	2	2019	6Diax12	13.4	28.28	94	7450	Non Engraved
3	4000Psi, Share W.	22	2	2019	6Diax12	13.8	28.28	83	6580	Non Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Muhammad Moutsim, Project Manager (BMCL) Banu Mukhtar

Project: Construction of Tariq Float Glass Package-II. (Hydrogen Station Pad)

Our Ref. No. CL/CED/	7833	Dated:	15-04-19
Your Ref. No.	Nil	Dated:	05-04-19

Tested on:

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-**04**-19

11-04-19 in dry/wet condition

Casting Date\* Size Weight Area of Ultimate Ultimate ° Z X-Mark\* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ທັ (gms) (Sq. in) (Tons/lbs) (Psi) 1 3750 Psi 30 3 2019 6x6x6 8.4 36 83 5170 Non Engraved 3750 Psi 2 30 3 2019 6x6x6 8.6 36 62 3860 Non Engraved End ---\_\_\_ 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Muhammad Moutsim, Project Manager (BMCL) To: **Banu Mukhtar**

Project: Construction of Tariq Float Glass Package-II. (Chimney, Circular Wall)

Our Ref. No. CL/CED/	7834	Dated:	15-04-19
Your Ref. No.	Nil	Dated:	05-04-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-**04**-19 Tested on:

11-04-19 in dry/wet condition

<b>I</b>		<u> </u>				[	[			]
ć		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(grr	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4375 Psi	7	3	2019	6x6x6	8.4	36	75	4670	Non Engraved
2	4375 Psi	7	3	2019	6x6x6	8.6	36	88	5480	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Muhammad Moutsim, Project Manager (BMCL) Banu Mukhtar

Project: Construction of Tariq Float Glass Package-II. (Furnace Oil Tank Footing)

Our Ref. No. CL/CED/	7835	Dated:	15-04-19
Your Ref. No.	Nil	Dated:	05-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-04-19 Tested on:

11-04-19 in dry/wet condition

Casting Date\* Size Weight Area of Ultimate Ultimate o Z Х-Mark\* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ທັ (Tons/lbs) (gms) (Sq. in) (Psi) 7 1 3750 Psi 3 2019 6x6x6 8.4 36 85 5290 Non Engraved 2 7 3 2019 5040 3750 Psi 6x6x6 36 Non Engraved 8.6 81 End ------4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

#### **Director/Dy. Director Concrete Laboratory**



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Muhammad Moutsim, Project Manager (BMCL) Banu Mukhtar

Project: Construction of Tariq Float Glass Package-II. (Furnace Oil Tank Footing)

Our Ref. No. CL/CED/	7836	Dated:	15-04-19
Your Ref. No.	Nil	Dated:	<b>05</b> -04-19

Tested on:

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-**04**-19

11-04-19 in dry/wet condition

Casting Date\* Size Weight Area of Ultimate Ultimate ° Z X-Mark\* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ທັ (gms) (Sq. in) (Tons/lbs) (Psi) 1 4375 Psi 28 3 2019 6x6x6 8.4 36 81 5040 Non Engraved 4375 Psi 28 3 2019 5600 2 6x6x6 8.6 90 Non Engraved 36 End ---\_\_\_\_ \_\_\_ 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Muhammad Yaseen. To:

8407 Dr. Aqsa

Equator Engineering Services, Chak Shehzad

Project: CMPAK Site ID-5182	•	ODU Foundati	ions.
Our Ref. No. CL/CED/	7837	Dated:	15-04-19

Your Ref. No.	Equator/Cubes/CMPAK/019	Dated:	08-04-19

#### COMPRESSION TEST REPORT

Tested on:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-**04**-19

11-04-19 in dry/wet condition

		1								
		Ca	asting	J Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		1	4	2019	6x6x6	8	36	88	5480	Non Engraved
2		1	4	2019	6x6x6	8.2	36	92	5730	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Imran Akhtar, Project Manager To: CM Engineering Pvt. Ltd.

8408 Dr. Aqsa

Project: CMPAK Site ID-42626, Pier Foundation

Our Ref. No. CL/CED/ 7838 Dated: 15-04-19

Tested on:

Your Ref. No. CME/Cubes/CMPAK/493 Dated: 03-04-19

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-**04**-19

11-04-19 in dry/wet condition

<b></b>		1			1					1
Sr. No.		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		6	3	2019	6x6x6	8.4	36	89	5540	Non Engraved
2		6	3	2019	6x6x6	8.2	36	96	5980	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Imran Akhtar, Project Manager To: CM Engineering Pvt. Ltd.

8408 Dr. Aqsa

Project: CMPAK Site ID-42628, Pier Foundation

Our Ref. No. CL/CED/ 7839 Dated: 15-04-19

Tested on:

Your Ref. No. CME/Cubes/CMPAK/492 Dated: 04-04-19

## **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-**04**-19

11-04-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight		Size (in)	Weight (Ibs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks	
			(grr	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		7	3	2019	6x6x6	8.4	36	83	5170	Non Engraved
2		7	3	2019	6x6x6	8	36	86	5360	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Imran Akhtar, Project Manager To: CM Engineering Pvt. Ltd.

8408 Dr. Aqsa

# Project: CMPAK Site ID-41518, Raft

Our Ref. No. CL/CE	ED/	7840	Dated:	15-04-19
Your Ref. No.	CME/0	Cubes/CMPAK/490	Dated:	<b>04</b> -04-19

Tested on:

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-**04**-19

11-04-19

in dry/wet condition

		0		D-1-+	0:		A		1.000	
ö		Ca	isting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	Vet W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		7	3	2019	6x6x6	8.2	36	94	5850	Non Engraved
2		7	3	2019	6x6x6	8.4	36	93	5790	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### Imran Akhtar, Project Manager To: CM Engineering Pvt. Ltd.

8408 Dr. Aqsa

## Project: CMPAK Site ID-41518, Column

Our Ref. No. CL/CED/	7841	Dated:	15-04-19

Tested on:

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-**04**-19

11-04-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight		Size (in)	Weight (lbs./gms)	Area of X-	Ultimate load	Ultimate Stress	Remarks	
Sr.	Mark	/ •			(11)	(ibs./giiis)	Section			Remains
			(gr	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		9	3	2019	6x6x6	8.4	36	75	4670	Non Engraved
2		9	3	2019	6x6x6	8	36	88	5480	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Major (Muhammad Farhan Khan), Project Officer Dr

8415

Dr. Asad Gillani

**19 Engineer Battalion (Chaghai Sappers), Sheikhupura Camp C/O Signal Centre, FWO Chaklala.** Project: Kot Abdul Malik Bridge (South Bound) at M-2. (M/S Trust Developers & Constt. Pvt. Ltd.)

Our Ref. No. CL/CED	/ 7842	Dated:	15-04-19
Your Ref. No.	607/SDO B&R/General	Dated:	05-04-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

08-04-19 Tested on:

11-04-19 in dry/wet condition

						1		•	•		
			Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)		
1		30	3	2019	6Diax12	14.2	28.28	65	5150	Non Engraved	
2		30	3	2019	6Diax12	14.4	28.28	83	6580	Non Engraved	
3		30	3	2019	6Diax12	14	28.28	77	6100	Non Engraved	
End											
5											
6											
7											
8											
9											
10											
11											
12											
13											
14											
15											
16											

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)