

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Arfan ul Haq,RE,NESPAK Pvt. Ltd.Highways and Transportation Enggg. Section, To: Islamabad.

Dr. Umbreen

8455

Conc. Post for Fence Manuf. by Semco & Power Line Quick Conc. Company Islamabad. Project:(CPEC),West. Route Hakla (on M1)~Yarak(D.I.Khan) Motorway,Pack.-3(Tarap to Kot Balian)

 Our Ref. No. CL/CED/
 7923
 Dated:
 24-04-19

Your Ref. No. CPEC/NESPAK/PKG3/19/903 Dated:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-04-19

Tested on:

23-04-19 in dry/wet condition

13-04-19

		C	Casting Date* /Wet Weight		Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/We			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gms))			(Sq. in)	(Tons/lbs)	(Psi)	
1	Post Concrete				5.9X5.5X5.3	7	32.45	61	4220	Cut Piece
2	Post Concrete				5.9X5.5X5.3	6.8	32.45	61	4220	Cut Piece
3	Post Concrete				5.9X5.5X5.3	6.4	32.45	53	3660	Cut Piece
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 8456 Engr. Aamina

To: Mr. Nouman Rafique, Project Coordinator Seasole Construction Company. Masood Arcade, IJP Road, Islamabad. Project: Constt. of 16th Avenue Shopping Mall Gujranwala.

Our Ref. No. CL/CED/	7924	Dated:	24-04-19
Your Ref. No.	SS/HO/GUJ/LD/2019/14	Dated:	15-03-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		15- 04 -19		Tested on:		23-04-19	in dry/wet co	ondition		
No.			Casting Date*		Size	Weight	Area of X-	Ultimate	Ultimate	Pomorko
S.	IVIAIK	///	vel v	reigni	(11)	(ibs./gms)	Section	1080	Suess	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1		16	3	2019	6Diax12	13.2	28.28	47	3730	Non Engraved
2		16	3	2019	6Diax12	13	28.28	40	3170	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

8457 Dr. Aqsa

Buildings Sub Division No.12, Lahore. Project: Constt. of Office Complex of Food Directorate Divisi. Food Office Lahore & DFC, Office Lhr.

Our Ref. No. CL/CED/	7925	Dated:	24-04-19
Your Ref. No.	241/SDO 12th	Dated:	01-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		15-04-19		Tested on:		18 -04-19	in dry/wet c	ondition		
Sr. No.	Mark*	Ca /M	Casting Date*		Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Mumty Slab 5th F.	9	3	2019	6Diax12	13.2	28.28	80	6340	Non Engraved
2	Mumty Slab 5th F.	9	3	2019	6Diax12	13.2	28.28	72	5710	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

8457 Dr. Aqsa

Buildings Sub Division No.12, Lahore. Project:Constt. of Office Complex of Food Directorate Divisi. Food Office Lahore & DFC,Office Lhr.

CL/CED/	7926	Dated:	24-04-19
Your Ref. No.	283/SDO 12th	Dated:	13-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

15-04-19 Tested on:

18-04-19 in dry/wet condition

			Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	/Wet Weight (gms)		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
							(Sq. in)	(Tons/lbs)	(Psi)	
1	K2			3207	8.9x4.4x2.9	2944	39.16	61	3490	8.93
2	K2			3291	8.9x4.4x2.3	2986	39.16	43	2460	10.21
3	K2			3311	8.9x4.3x3	2977	38.27	42	2460	11.21
4	K2			3447	8.8x4.3x3	2992	37.84	27	1600	15.2
5	K2			3284	8.9x4.5x2.9	2980	40.05	35	1960	10.2
End										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8458

Dr. M. Yousaf

To:	Muhammad Tufail, Construction Team Leader Lahore Office.
	Zor Engineers Pvt. Ltd.
	Project:Good Shepherd Christian Hospital, Kasur.

 Our Ref. No. CL/CED/
 7927
 Dated:
 24-04-19

 Your Ref. No.
 230.28.1/MT/15
 Dated:
 15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-**04**-19 Tested on: 19-04-19 in dry/wet condition Ultimate Weight Ultimate Casting Date* Size Area of Š Х-/Wet Weight Mark* (lbs./gms) Stress Remarks (in) load Section ົດ. (gms) (Sq. in) (Tons/lbs) (Psi) 1 1st Floor Slab 14 3 2019 6x6x6 36 46 2870 Non Engraved 82 2 1st Floor Slab 14 3 2019 6x6x6 8.2 36 44 2740 Non Engraved End ____ ____ ____ 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8459

Dr. Aqsa

To: Sub Divisional Officer Buildings Sub Division No.9, Lahore. Project: Construction of Provincial Police Lines Highway Patrol at Jia Bagga Lahore. Our Ref. No.

CL/CED/	7928	Dated:	24-04-19
Your Ref. No.	46/9th	Dated:	27-03-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received
on:15-04-19Tested on:18-04-19in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Ŵ	Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	ABC			3320	8.8x4.3x2.9	3040	37.84	52	3080	9.21
2	ABC			3357	8.8x4.3x2.9	3077	37.84	53	3140	9.09
3	ABC			3483	8.8x4.4x2.9	3096	38.72	44	2550	12.5
4	ABC			3496	8.9x4.3x2.8	3144	38.27	46	2700	11.19
5	ABC			3497	8.7x4.4x2.9	3089	38.28	37	2170	13.2
6	ABC			3461	8.9x4.4x2.9	3064	39.16	38	2180	12.95
End										
8								_	_	
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: M. Ali Ghaffar, G.M Operations

8461 Dr. Umbreen

Punjab Tiles, 43-Tipu Block, (LDA) New Garden Town, Ferozepur Road, Lahore. Project:

Our Ref. No. CL/CED/	7929	Dated:	24-04-19
Your Ref. No.	Nil	Dated:	15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-04-19 Tested on: 17-04-19 in dry/wet condition

			.							
ġ			Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/W	et W	eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Terrazzo Tile				5.9x5.9x1	1342	34.81	77	4960	
2	Terrazzo Tile				5.8x5.9x1	1396	34.22	83	5440	
3	Terrazzo Tile				5.8x5.9x1	1371	34.22	75	4910	
4	Terrazzo Tile				5.9x5.9x1	1377	34.81	81	5220	
End										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Го:	Mr. Muhammad Yaseen Equator Engineering Servic Project: CMPAK, Site ID-51	ces Chak Shehzad 989, Tower, DG ar	l. Id ODU Found	ations
	Our Ref. No. CL/CED/	7930	Dated:	24-04-19

Your Ref. No. Equator/Cubes/CMPAK/019 Dated: 10-04-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

17**-04**-19

22-04-19 in dry/wet condition

8474

Engr. A. Rehman

			Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1		3	4	2019	6x6x6	8	36	90	5600	Non Engraved
2		3	4	2019	6x6x6	8	36	88	5480	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

8474

Engr. A. Rehman



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Yaseen Equator Engineering Services Chak Shehzad. Project: CMPAK, Site ID-51896, Tower, DG and ODU Foundations

Our Ref. No. CL/CED/	7931	Dated:	24-04-19

Your Ref. No. Equator/Cubes/CMPAK/019 Dated: 15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-04-19 Tested on: 22-04-19 in dry/wet condition

	Mark*	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No		N	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		18	3	2019	6x6x6	8.2	36	97	6040	Non Engraved
2		18	3	2019	6x6x6	8.2	36	108	6720	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering Pvt. Ltd. Project: CMPAK, Site ID-42673

8475 Engr. A. Rehman

Our Ref. No. CL/C	ED/	7932	Dated:	24 -04-19
Your Ref. No.	CME/C	ubes/CMPAK/495	Dated:	12 -04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

17-04-19 Tested on:

22-04-19 in dry/wet condition

		Са	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	OZ Mark*		/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gn	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column	5	4	2019	6x6x6	8.2	36	101	6290	Non Engraved
2	Column	5	4	2019	6x6x6	8.2	36	91	5670	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering Pvt. Ltd. Project: CMPAK, Site ID-42673 8475 Engr. A. Rehman

Our Ref. No. CL/0	CED/	7933	Dated:	24-04-19
Your Ref. No.	CME/C	Cubes/CMPAK/494	Dated:	10-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

17-04-19 Tested on:

22-04-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	N	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Raft	3	3 4 2019		6x6x6	8	36	113	7040	Non Engraved
2	Raft	3	4	2019	6x6x6	8.2	36	100	6230	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

8475

Engr. A. Rehman



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering Pvt. Ltd. Project: CMPAK, Site ID-41526

Our Ref. No. CL/CED/	7934	Dated:	24-04-19
Your Ref. No.	CME/Cubes/CMPAK/497	Dated:	12-04-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

17-04-19

22-04-19 in dry/wet condition

Sr. No.	Mark*	Ca M	Casting Date* /Wet Weight (gms)		Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Pier Foundation	15	3	2019	6x6x6	8.8	36	93	5790	Non Engraved
2	Pier Foundation	15	3	2019	6x6x6	8.4	36	98	6100	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

8475 Engr. A.

Rehman



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering Pvt. Ltd. Project: CMPAK, Site ID-42627

Our Ref. No. CL/CED/	7935	Dated:	24-04-19
Your Ref. No.	CME/Cubes/CMPAK/496	Dated:	10-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-04-19 Tested on: 22-04-19 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Pier Foundation	13	3	2019	6x6x6	8	36	109	6790	Non Engraved
2	Pier Foundation	13	3	2019	6x6x6	8.2	36	110	6850	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

supervisor(lab)



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering Pvt. Ltd. Project: CMPAK, Site ID-42643, Complet Foundation

8477 Engr. A. Rehman

Our Ref. No. CL/CE	ED/	7936	Dated:	24-04-19
Your Ref. No.	CME/Cu	bes/CMPAK/498	Dated:	18-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-04-19 Tested on:

.....

22-04-19 in dry/wet condition

			Casting Date* /Wet Weight		Size	Weight	Area of	Ultimate	Ultimate	
Nark*		M			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		21	3	2019	6x6x6	8.4	36	107	6660	Non Engraved
2		21	3	2019	6x6x6	8.6	36	121	7530	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength Note: Above results pertain to the unsealed samples supplied to the laboratory

supervisor(lab)



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Cresent Conrete Pvt. Ltd. 24-KM Multan Road, Near Amrat Cola, Lahore. Project:

 Our Ref. No. CL/CED/
 7937
 Dated:
 24-04-19

 Your Ref. No.
 Nil
 Dated:
 08-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

16-04-19 Tested on:

17-04-19 in dry/wet condition

8462

Dr. Umbreen

			ootin	~						
			asun Date	ıg ∗	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight		nt	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms))			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular, Grey				7.8x3.8x2.3	2864	29.64	83	6280	
2	Rectangular, Grey				7.8x3.8x2.3	2856	29.64	63	4770	
3	Rectangular, Grey				7.8x3.8x2.3	2888	29.64	63	4770	
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength Note: Above results pertain to the unsealed samples supplied to the laboratory

supervisor(lab)

8507

Engr. Ubaid



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: (Khalid Bashir) Ittefaq Building Solutions Pvt. Ltd. Project: NBH Renovation, Lahore.

Our Ref. No. CL/CED/	7938	Dated:	24-04-19
Your Ref. No.	IBS/NISHAT/BT02	Dated:	23-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

23-04-19 Tested on:

24-04-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight (gms)		Casting Date* /Wet Weight (gms)		ig ht	Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Hollow Block				11.9x5.75x7.6	18	53.23	29	1230			
2	Hollow Block				11.9x5.75x7.6	16.4	53.23	59	2490			
End												
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8463 Dr. Umbreen

To: Muhammad Saleem, GM Professional Construction Services Pvt. Ltd. Project: Windsor Inn Hotel Multan.

Our Ref. No. CL/CED/	7939	Dated:	24-04-19
Your Ref. No.	19/Eng-29	Dated:	15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-04-19 Tested on: 16-04-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	et W	eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Basement Slab	12	3	2019	6Diax12	14	28.28	33	2620	Non Engraved
2	Basement Slab	12	3	2019	6Diax12	13.4	28.28	65	5150	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

supervisor(lab)



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Engr. Adnan Akmal, Project Co-ordinator SINACO Engineers Pvt. Ltd.

8464 Dr. M. Yousaf

Project: Construction	of Tariq Float Gla	ss Plant at Shei	khupura.
Our Ref. No. CL/CED/	7940	Dated:	24-04-19

Your Ref. No.	SEL/LHR/C-461/9972	Dated:	15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

16-04-19 Tested on:

19-04-19 in dry/wet condition

r										
		Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	A-L-S	30	3	2019	6x6x6	8.4	36	84	5230	Non Engraved
2	A-L-S	30	3	2019	6x6x6	8.6	36	64	3990	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Engr. Adnan Akmal, Project Co-ordinator SINACO Engineers Pvt. Ltd. Project: Construction of Tarig Float Glass

8464 Dr. M. Yousaf

SINACO Engineers FVI. Ltd.										
Project: Construction of	f Tariq Float Gla	ass Plant at She	eikhupura.							
Our Ref. No. CL/CED/	7941	Dated:	24 -04-19							

Your Ref. No. SEL/LHR/C-461/9973 Dated: 15-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

16-04-19 Tested on:

19-04-19 in dry/wet condition

_		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
ir. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
S			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	FUR / B-B	11	3	2019	6x6x6	8.4	36	64	3990	Non Engraved
2	FUR / B-B	11	3	2019	6x6x6	8.6	36	110	6850	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Shanawar Ali, Resident Engineer Javed I Mirza & Associates.

Project: Construction of Sheikh Jasim Boys & Girls School at Bharerri, District Jhang.

Our Ref. No. CL/CED/	7942	Dated:	24-04-19
Your Ref. No.	JIM/Bhakkar/TTT-01/19	Dated:	16-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

16-04-19 Tested on:

17-0

17-04-19 in dry/wet condition

8465

Dr. Umbreen

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Uni Block, Red	18	3	2019	2.3 thick	2960	37.25	110	6620	
2	Uni Block, Grey	18	3	2019	2.3 thick	2989	37.25	81	4880	
3	Uni Block, Grey	18	3	2019	2.3 thick	2899	37.25	84	5060	
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

supervisor(lab)

Director/Dy. Director Concrete Laboratory

8466

Engr. Aamina



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Abdul Ghafoor, Karol War, Post Office Baghbanpura, Lahore Cantt. Swift Construction Company. Project: Bank Alfalah Building, 107-Y, Commercial Area, Phase-3, DHA, Lahore.

Our Ref. No. CL/CED/ 7943 Dated: 24-04-19

Your Ref. No. Nil Dated: 16-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

16-04-19 Tested on:

23-04-19 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1		8	4	2019	6Diax12	14	28.28	37	2940	Engraved
2		8	4	2019	6Diax12	14	28.28	35	2780	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8481

Engr. Aamina

Muhammad Ramzan Construction. 43 Tipu Block, New Garden Town, (LDA), Ferozepur Road, Laahore. Project: UMER Masjid Faisalabad.

Our Ref. No. CL/CED/	7944	Dated:	24 -04-19
Your Ref. No.	Nil	Dated:	18 -04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

To: Engr. Muhammad Waqas Ramzan, Director

Specimens received on:

18-04-19 Tested on:

23-04-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight (gms)		Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks	
1	F.F Slab	15	2	2019	6x6x6	8.4	36	69	4300	Engraved
2	F.F Slab	15	2	2019	6x6x6	8.6	36	58	3610	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Muhammad Imran, Resident Engineer

8482 Engr. Aamina

G3 Engineering Consultants Pvt. Ltd. PSIC House Davis Road, Lahore. Project: Consultancy Services for Review & Vetting of all Documents, i.e. Planning, Designing, PC-1, Estimates

Our Ref. No. CL/CED/	7945	Dated:	24-04-19
Your Ref. No.	G3/0161	Dated:	18-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-04-19 Tested on:

23-0

23-04-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Slab	18	3	2019	6Diax12	13.2	28.28	36	2860	Engraved
2	1st Floor Slab	18	3	2019	6Diax12	13.4	28.28	36	2860	Engraved
3	1st Floor Slab	18	3	2019	6Diax12	13.4	28.28	35	2780	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

8496

Engr. Aamina



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Assistant Engineer

Dry Port Headquarter, Lahore. (M/S Al-Arab Associates.)

Project: Rehablitation/Improvement of Lahore Dry Port Mughalpura (Balance Civil & Electrical Works).Our Ref. No. CL/CED/7946Dated:24-04-19

Your Ref. No.	524/M	Dated:	17-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-**04**-19 Tested on: 23-04-19 in dry/wet condition Area of Ultimate Ultimate Casting Date* Size Weight Š X-/Wet Weight Mark* (in) (lbs./gms) load Stress Remarks Section <u>ت</u>. (Sq. in) (Tons/lbs) (Psi) (gms) 1 Floor Yard 27 2 2019 6x6x6 8.4 36 65 4050 Non Engraved 2 Floor Yard 27 2 2019 6x6x6 36 35 2180 Non Engraved 8.4 3 27 2 Floor Yard 2019 6x6x6 36 5360 8.6 86 Non Engraved End -------------------------____ 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab) **Department of Civil Engineering** University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217 Engr. A. Rehman

To: Sub Divisional Officer

Buildings Sub Division Sheikhupura. Project: Constt. of PHP at Jhabran Hafizabad Road Tehsil Shekhupura District Sheikhupura. Our Ref. No. CL/CED/ 7947 Dated: 24-04-19

Your Ref. No.	4337/S	Dated:	05-03-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-**04**-19 Tested on: 22-04-19 in dry/wet condition Casting Date* Size Area of Ultimate Ultimate Weight Š /Wet Weight Mark* (in) (lbs./gms) X-Section load Stress Remarks <u>ت</u>. (Tons/lbs) (gms) (Sq. in) (Psi) 1 Column 4 3 2019 6x6x6 8 36 92 5730 Non Engraved 2 Column 4 3 2019 6x6x6 36 103 6410 Non Engraved 8.2 End --------------------____ ____ ____ 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Plain and Reinforced Concrete Laboratory



Director/Dy. Director Concrete Laboratory

8497

Note: Above results pertain to the unsealed samples supplied to the laboratory The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)