

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 9094 Dr. Umbreen

Central Civil Division No.II, Pak P.W.D., Lahore Project: Construction of Wearhouse for Model Custom Collectorate at Thokar Niaz Baig, Lahore

Our Ref. No. CL/CED/	8781	Dated:	29-08-19
Your Ref. No.	AEE-I/CCD-II/LHR/39	Dated:	10-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

To: Shahid Raza Jafri (Assistant Executive Engineer-I)

Specimens received on:		22-08-19		l ested on:		28-08-19	In dry/wet condition			
lo.		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. N	Mark*	/W	'et V	Veight	(in)	(lbs./gms)	Section	load	Stress	Remarks
-		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1	Columns (Basement)	11	6	2019	6x6x6	8.2	36	94	5850	Non Engraved
2	Columns (Basement)	11	6	2019	6x6x6	8.2	36	98	6100	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Shahid Raza Jafri (Assistant Executive Engineer-I) Central Civil Division No.II, Pak P.W.D., Lahore

9094 Dr. Umbreen

Project: Construction of Wearhouse for Model Custom Collectorate at Thokar Niaz Baig, Lahore

Our Ref. No. CL/CED/	8782	Dated:	29-08-19
Your Ref. No.	AEE-I/CCD-II/LHR/39A	Dated:	15-07-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

22-08-19

28-08-19 in dry/wet condition

		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et \	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Beams & Slab (Basement)	16	6	2019	6x6x6	8	36	45	2800	Non Engraved
2	Beams & Slab (Basement)	16	6	2019	6x6x6	8	36	65	4050	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Altaf Hussain (M.E) M/s AS Enterprises (AA Associats)

Project: Style Textile Mill

Our Ref. No. CL/CED/	8783	Dated:	29-08-19
Your Ref. No.	USD/ASE/17	Dated:	25-08-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

26-08-19

28-08-19 in dry/wet condition

9099

Dr. Umbreen

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	Ŵ	'et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)	0		(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	C-30 (Upstand Beam)	24	7	2019	6x6x6	8.4	36	81	5040	Non Engraved
2	C-30 (Upstand Beam)	24	7	2019	6x6x6	8.4	36	73	4550	Non Engraved
3	C-30 (Upstand Beam)	24	7	2019	6x6x6	8.6	36	84	5230	Non Engraved
4	C-20(Slab of Knitting Building)	24	7	2019	6x6x6	8.4	36	63	3920	Non Engraved
5	C-20(Slab of Knitting Building)	24	7	2019	6x6x6	8.4	36	47	2930	Non Engraved
6	C-20(Slab of Knitting Building)	24	7	2019	6x6x6	8.4	36	63	3920	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Zia-UI-Islam Khan Suri (Asstt: Executive Engineer-IV) Dr. Aqsa Central Civil Division No.II, Pak P.W.D., Lahore Project: Construction of Additional Floor on Existing Transit Accommodation (Inland Revenue) Stuluj **Block Allama Iqbal Town, Lahore** Ir Rof No. CL/CED/ 0704 Dated 20 00 10

Our Ref. No. CL/CED/	8784	Dated:	29-08-19
Your Ref. No.	AEE-IV/LCCD-II/25	Dated:	10-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

27-08-19 Tested on:

29-08-19 in dry/wet condition

		(Cast Dat	ting :e*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/W	/Wet Weight (gms)		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
							(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:2:4)	10	6	2019	6x6x6	8.4	36	70	4360	Non Engraved
2	(1:2:4)	10	6	2019	6x6x6	8.4	36	75	4670	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

9111



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Zia-UI-Islam Khan Suri (Asstt: Executive Engineer-IV) Dr. Aqsa Central Civil Division No.II, Pak P.W.D., Lahore Project: Construction of Additional Floor on Existing Transit Accommodation (Inland Revenue) Stuluj **Block Allama Iqbal Town, Lahore**

Our Ref. No. CL/CED/	8785	Dated:	29-08-19
Your Ref. No.	AEE-IV/LCCD-II/24	Dated:	10-07-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

27-08-19

29-08-19 in dry/wet condition

		C	astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	٨	Net	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:1.5:3)	8	5	2019	6x6x6	8.8	36	83	5170	Non Engraved
2	(1:1.5:3)	8	5	2019	6x6x6	8.8	36	83	5170	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

9111



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Arslan Arshad (Project Manager)

DEPAC, Lahore

Project: Construction of Dr. Maqbool Ahmad Block, Kng Edward Medical University (KEMU), Lahore

Our Ref. No. CL/CED/	8786	Dated:	29-08-19
Your Ref. No.	T-03/24/1	Dated:	23-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

24-07-19

Specimens received on:

Tested on:

29-08-19 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	В		8.9x4.4x2.9	3310	39.16	27	1550	
2	В		9.0x4.4x3.0	3304	39.6	49	2780	
3	В		8.9x4.4x2.9	3392	39.16	47	2690	
4	В		8.9x4.4x3.0	3320	39.16	61	3490	
5	В		8.9x4.4x3.0	3334	39.16	59	3380	
6	В		8.9x4.4x2.9	3216	39.16	47	2690	
7	В		8.9x4.4x3.0	3290	39.16	53	3040	
8	В		8.9x4.4x3.0	3251	39.16	43	2460	
9	В		8.9x4.4x2.9	3343	39.16	58	3320	
10	В		8.9x4.4x2.9	3352	39.16	43	2460	
11								
12								
13								
14								
15								
16								

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the

engineer.

Director/Dy. Director Concrete Laboratory

8976 Dr. Aqsa



Kasur

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer Buildings Sub Division

9023 Dr. Aqsa

Project: Construction of Ware House at Chief Executive Officer District Health Authority, Kasur

Our Ref. No. CL/CED/	8787	Dated:	29-08-19
Your Ref. No.	798	Dated:	29-06-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

01-08-19 Tested on:

29-08-19 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	A B C		8.9x4.3x2.9	3205	38.27	36	2110	
2	ABC		8.8x4.4x2.9	3265	38.72	47	2720	
3	ABC		8.9x4.4x2.9	3315	39.16	37	2120	
4	ABC		8.9x4.3x2.9	3295	38.27	51	2990	
5	ABC		8.9x4.4x2.9	3211	39.16	44	2520	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Engr. Imran Zahid (A. Senior Engineer)

9028 Dr. Aqsa

University of Education, Lahore (M/s Weog Global)

Project: Construction of Warden House at UE Township Campus

Our Ref. No. CL/CED/	8788	Dated:	29-08-19
Your Ref. No.	UE/Engg/CE/2019/452	Dated:	31-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

01-08-19 Tested on: 29-08-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Size (in)	Weight (Ibs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Μ		8.9x4.4x2.9	3192	39.16	52	2980	
2	Μ		8.8x4.4x2.9	3120	39.16	55	3150	
3	Μ		8.9x4.3x2.9	3153	38.27	45	2640	
4	Μ		8.8x4.4x2.9	3164	38.72	49	2840	
5	Μ		8.9x4.4x2.9	3122	39.16	60	3440	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Resident Engineer

9090 Dr. Aqsa

G3 Engineering Consultants (Pvt.) Ltd. Lahore Project: Construction of Academic Block 1 & 2 HH Campus University of Gujrat						
Our Ref. No. CL/CED/	8789	Dated:	29-08-19			

Your Ref. No.	G3EC/UOG/155	Dated:	31-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

22-08-19 Tested on:

29-08-19 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.8x3.8x2.2	2736	29.64	120	9070	
2	Rectangular Grey		7.8x3.8x2.2	2737	29.64	136	10280	
3	Rectangular Grey		7.8x3.8x2.2	2676	29.64	126	9530	
4	Rectangular Grey		7.8x3.8x2.2	2822	29.64	142	10740	
5	Rectangular Red		7.8x3.8x2.2	2627	29.64	148	11190	
6	Rectangular Red		7.8x3.8x2.2	2655	29.64	152	11490	
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

9092 Dr. Aqsa

Public Health Engg: Sub Division, Toba Tek Singh Project: Laying of PCC, Tuff Tiles, Soling & Resoling, Drain, Repair of Roads and Pipelines of Water and Sewerage in District T.T.Singh (M/s Chaudhary Traders)

Our Ref. No. CL/CED/	8790	Dated:	29-08-19
Your Ref. No.	107/PHE-SD-TTS	Dated:	25-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

22-08-19 Tested on:

29-08-19 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. Nc	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.7x3.8x2.8	3495	29.26	91	6970	
2	Rectangular Grey		7.7x3.8x2.8	3509	29.26	111	8500	
3	Rectangular Grey		7.7x3.8x3.0	3454	29.26	92	7050	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

Public Health Engg: Sub Division, Toba Tek Singh

Project: Laying of Soling, Drain, Repair of Roads, Water Suply Pipelines and Sewerage in District T.T.Singh (M/s Muhammad Hanif Anjum Traders)

Our Ref. No. CL/CED/	8791	Dated:	29-08-19
Your Ref. No.	158/PHE-SD-TTS	Dated:	25-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

22-08-19 Tested on:

29

29-08-19 in dry/wet condition

_		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.7x3.8x2.8	3492	29.26	107	8200	
2	Rectangular Grey		7.7x3.8x3.0	3501	29.26	105	8040	
3	Rectangular Grey		7.7x3.8x3.0	3524	29.26	96	7350	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

9092 Dr. Aqsa