

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To:Engr. Muhammad Abdullah (Assistant Engineer)
B&W Department, UET
Lahore
Project:Construction Site of Extension of Admin Block in UET LahoreDr. Was
Dr. Was
Our Ref. No. CL/CED/Our Ref. No. CL/CED/7371Dated:27-02-19

Your Ref. No. B&W/AENC/702 Dated: 04-02-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-02-19 Tested on:

27-02-19 in dry/wet condition

Casting Date* Size Weight Area of Ultimate Ultimate Š Х-Mark* /Wet Weight (in) (lbs./gms) load Stress Remarks Section . . (gms) (Sq. in) (Tons/lbs) (Psi) 1 **Plinth Beams** 7 1 2019 6Diax12 13.6 28.28 110 8720 Non Engraved 2 **Plinth Beams** 7 1 2019 6Diax12 13.4 28 28 100 7930 Non Engraved End ___ -------------------------4 5 6 7 8 9 10 11 12 13 14 15

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

16

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to

be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

8078 Dr. Waseem Abbas



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Waseem G. Rasool To:

8111 Engr.Ubaid Ahmed

Al-Habib Construction Company Pvt. Ltd. Lahore Project:U900 Karachi & Lahore, Site ID CI-1700, Tower Column Foundation

Tested on:

Our Ref. No. CL/CED/	7372	Dated:	27-02-19
Your Ref. No.	AHCC/Ufone/D7/1700	Dated:	12-02-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-19 in dry/wet condition

		Casting Da		Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		12	1	2019	6x6x6	8	36	116	7220	Non Engraved
2		12	1	2019	6x6x6	7.9	36	96	5980	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Waseem G. Rasool To:

8111 Engr.Ubaid Ahmed

Al-Habib Construction Company Pvt. Ltd. Lahore Project:U900 Karachi & Lahore, Site ID CI-1700, Tower Raft Foundation

Our Ref. No. CL/CED	/ 7373	Dated:	27-02-19
Your Ref. No.	AHCC/Ufone/D7/1700	Dated:	12-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		10	1	2019	6x6x6	8.2	36	114	7100	Non Engraved
2		10	1	2019	6x6x6	8	36	130	8090	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Waseem G. Rasool

8111 Engr.Ubaid Ahmed

AI-Habib Construction Company Pvt. Ltd. Lahore Project:CMPAK GSM Phase-IX, Site ID 42615, ODU BTS Foundation

Our Ref. No. CL/CE	D/	7374	Dated:	27-02-19
Your Ref. No.	AHCC/CMPA	K/D7/42615	Dated:	18-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-19 in dry/wet condition

-19 in ary/wet condition

		Casting Date*		Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		8	2	2019	6x6x6	7.8	36	71	4420	Non Engraved
2		8	2	2019	6x6x6	8	36	57	3550	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Waseem G. Rasool

8111 Engr.Ubaid Ahmed

Al-Habib Construction Company Pvt. Ltd. Lahore Project:CMPAK GSM Phase-IX, Site ID 42611, ODU BTS Foundation

Our Ref. No. CL/CEI	D/ 7375	Dated:	27-02-19
Your Ref. No.	AHCC/CMPAK/D7/42611	Dated:	12-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-1

25-02-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//	Vet W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		3	2	2019	6x6x6	8	36	104	6480	Non Engraved
2		3	2	2019	6x6x6	8	36	65	4050	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Waseem G. Rasool To:

8111 Engr.Ubaid Ahmed

Al-Habib Construction Company Pvt. Ltd. Lahore Project: CMPAK GSM Phase-IX, Site ID 42613, ODU BTS Foundation

Our Ref. No. CL/CE	0/ 7376	Dated:	27-02-19
Your Ref. No.	AHCC/CMPAK/D7/42613	Dated:	12-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-19 in dry/wet condition

Sr. No.	Mark*			Date* /eight ns)	Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1		3	2	2019	6x6x6	8	36	92	5730	Non Engraved
2		3	2	2019	6x6x6	8	36	65	4050	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Waseem G. Rasool

8111 Engr.Ubaid Ahmed

AI-Habib Construction Company Pvt. Ltd. Lahore									
Project:CMPAK GSM Pr	Project:CMPAK GSM Phase-IX, Site ID 42657, ODU BTS Foundation								
Our Pof No. CL/CED/	7277	Datad:	27 02 10						

Our Rei. No. CL/CE	UI 1311	Dated.	27-02-19
Your Ref. No.	AHCC/CMPAK/D7/42653	Dated:	12-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-02-19

25-02-19 in dry/wet condition

Casting Date* Size Weight Area of Ultimate Ultimate ° Z Х-Mark* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ທັ (Tons/lbs) (gms) (Sq. in) (Psi) 1 3 2 2019 6x6x6 8 36 102 6350 Non Engraved 3 2 2019 2 6x6x6 36 102 6350 Non Engraved 8 End ---___ 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Retd. Colonel Azim Ilyas (Coordinator/Secretary) Lahore Diocesan Board of Education, Lahore Project:Cathedral School, 1-P Model Town, Lahore

Our Ref. No. CL/CED/	7378	Dated:	27-02-19
Your Ref. No.	COORD/124/43/BLDG	Dated:	18-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-02-19

22-02-19 in dry/wet condition

		<u> </u>								
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	R.C.C. Columns	15	1	2019	6x6x6	7.8	36	70	4360	Engraved
2	R.C.C. Columns	15	1	2019	6x6x6	7.6	36	94	5850	Engraved
3	R.C.C. Columns	12	1	2019	6x6x6	7.8	36	88	5480	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

8116 Dr. Aqsa



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

M. Saleem Construction Company To: Lahore Road, Sheikhupura

8121 Dr. Aqsa

Project:R.C.C Wall, G-2 to G-5 / Line-A to C

Our Ref. No. CL/CED/	7379	Dated:	27-02-19
Your Ref. No.	Nil	Dated:	19-02-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-02-19 Tested on: 22-02-19

in dry/wet condition

		r								
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		13	2	2019	6x6x6	9	36	115	7160	Engraved
2		13	2	2019	6x6x6	9	36	85	5290	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Deputy Director (QCD) To:

8133 Dr. Aqsa

WASA, LDA, Lahore / M/s. Aijaz Corporation Project:Tender No.XEN/O&M-II/RT2018-19/48-Rehabilitation of Shahdra Drain at Pindi Das Road

Our Ref. No. CL/CED/	7380	Dated:	27-02-19
Your Ref. No.	QCD/153	Dated:	16-02-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

20-02-19 Tested on:

22-02-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RCC (1:2:4)	23	1	2019	6x6x6	8.9	36	30	1870	Engraved
2	RCC (1:2:4)	23	1	2019	6x6x6	8.4	36	22	1370	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



Plain and Reinforced Concrete Laboratory **Department of Civil Engineering**

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (Tech),

8168 Dr. Umbreen

Anti Corruption Establishment Faisalabad Region, Faisalabad Project: Enquiry No.794/2018 Against Public Health Department Chiniot Regarding Scheme Tuff Tile in Mohallah Ghaiziabad Chiniot

Our Ref. No. CL/CED/	7381	Dated:	27-02-19
Your Ref. No.	DDT-ACE-FSD- 2019/239	Dated:	15-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

27-02-19 Specimens received on:

27-02-19 in dry/wet condition

Casting Ultimate Size Weight Area of Ultimate Date* å /Wet Х-Remarks Mark* (in) (lbs./gms) load Stress Weight Section ົດ. (gms) (Sq. in) (Tons/lbs) (Psi) 2.4 Thick 1 3509 37.25 144 8660 Uniblock Grey 2.4 Thick 37.25 2 Uniblock Grey 3492 150 9030 3 Uniblock Red 2.4 Thick 37.25 132 7940 3450 4 Uniblock Red 2.4 Thick 3453 37 25 140 8420 End ---6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

Tube Well Sub Division, Daudkhel

8123 Engr.Ubaid Ahmed

Project: Channelization of Rakka and Darsola Nullahs in Tehsil ISA Khel Distt. Mianwali

Our Ref. No. CL/CED/	7382- 1 of 2	Dated:	27-02-19
Your Ref. No.	396-99/4-W	Dated:	14-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-02-19

25-02-1

25-02-19 in dry/wet condition

1		1						1		
ວ່ 2 Mark* ເວັ		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
		/W	/et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Pannel No. 7	14	1	2019	6x6x6	8.1	36	49	3050	Non Engraved
2	Pannel No. 7	14	1	2019	6x6x6	8.1	36	53	3300	Non Engraved
3	Pannel No. 8	14	1	2019	6x6x6	8	36	49	3050	Engraved
4	Pannel No. 8	14	1	2019	6x6x6	8	36	59	3680	Engraved
5	Pannel No. 9	15	1	2019	6x6x6	8.4	36	65	4050	Engraved
6	Pannel No. 9	15	1	2019	6x6x6	8.4	36	63	3920	Engraved
7	Pannel No. 10	16	1	2019	6x6x6	8.4	36	69	4300	Engraved
8	Pannel No. 10	16	1	2019	6x6x6	8.4	36	55	3430	Engraved
9	Pannel No. 01	17	1	2019	6x6x6	8.6	36	96	5980	Engraved
10	Pannel No. 01	17	1	2019	6x6x6	8.4	36	97	6040	Engraved
11	Pannel No. 11	17	1	2019	6x6x6	8.6	36	86	5360	Engraved
12	Pannel No. 11	17	1	2019	6x6x6	8.4	36	44	2740	Engraved
13	Pannel No. 06	18	1	2019	6x6x6	8.6	36	87	5420	Engraved
14	Pannel No. 06	18	1	2019	6x6x6	8.2	36	67	4170	Engraved
15	Pannel No. 09	19	1	2019	6x6x6	8.6	36	75	4670	Engraved
16	Pannel No. 09	19	1	2019	6x6x6	8.4	36	83	5170	Engraved

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

Tube Well Sub Division, Daudkhel

8123 Engr.Ubaid Ahmed

Project: Channelization of Rakka and Darsola Nullahs in Tehsil ISA Khel Distt. Mianwali

Our Ref. No. CL/CED/	7382- 2 of 2	Dated:	27-02-19
Your Ref. No.	396-99/4-W	Dated:	14-02-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-02-19

25-0

25-02-19 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
17	Pannel No. 05	20	1	2019	6x6x6	8.6	36	85	5290	Engraved
18	Pannel No. 05	20	1	2019	6x6x6	8.6	36	71	4420	Engraved
19	Pannel No. 03	20	1	2019	6x6x6	8.4	36	84	5230	Engraved
20	Pannel No. 03	20	1	2019	6x6x6	8.4	36	79	4920	Engraved
21	Pannel No. 02	21	1	2019	6x6x6	8	36	50	3120	Non Engraved
22	Pannel No. 02	21	1	2019	6x6x6	8	36	45	2800	Non Engraved
23	Pannel No. 01	21	1	2019	6x6x6	8	36	51	3180	Non Engraved
24	Pannel No. 01	21	1	2019	6x6x6	8	36	51	3180	Non Engraved
End										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)