

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8981

Го: Muhammad Asif, General Manager

Dr. M. Yousaf

Sarfraz & Sons, Gajju Matta Stop, Lahore.

Project: Bhullay Shah Paper Mill.

Our Ref. No. CL/CED/ 8605 Dated: 25-07-19

Your Ref. No. Nil Dated: 24-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-07-19 Tested on: 25-07-19 in dry/wet condition

Ġ		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	//\	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Slab	26	6	2019	6x6x6	9	36	80	4980	Non Engraved
2	Slab	26	6	2019	6x6x6	8.6	36	95	5920	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8981

To: Muhammad Asif, General Manager

Dr. M. Yousaf

Sarfraz & Sons, Gajju Matta Stop, Lahore.

Project: Bhullay Shah Paper Mill.

Our Ref. No. CL/CED/ 8606 Dated: 25-07-19

Your Ref. No. Nil Dated: 24-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	etina	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Casting Date* /Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column	2	6	2019	6x6x6	8.8	36	98	6100	Non Engraved
2	Column	2	6	2019	6x6x6	8.6	36	95	5920	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8891

To: M/s AB Contractor Dr. M. Yousaf

Walton Road, Lahore Cantt.

Project:Foundation and Column Footings of MCB Branch at University Road Multan

Our Ref. No. CL/CED/ 8607 Dated: 25-07-19

Your Ref. No. ABC/2019/09-07/02 Dated: 09-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-07-19 Tested on: 25-07-19 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	//	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RCC Foundation	30	4	2019	6x6x6	9	36	78	4860	Engraved
2	RCC Footing Column	3	5	2019	6x6x6	9	36	66	4110	Engraved
3	RCC Footing Column	3	5	2019	6x6x6	8.6	36	76	4730	Engraved
4	RCC Plinth Beam	5	5	2019	6x6x6	9	36	73	4550	Non Engraved
5	RCC G.F. Column	21	5	2019	6x6x6	8	36	53	3300	Non Engraved
6	RCC G.F. Column	22	5	2019	6x6x6	9	36	58	3610	Engraved
7	RCC G.F. Floor Slab	1	6	2019	6x6x6	8.6	36	67	4170	Engraved
8	Vault Wall	9	6	2019	6x6x6	9	36	78	4860	Engraved
End										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8901

Dr. M. Yousaf

To: Imran Arshad (Sr. Project Manager)

Citi Housing (Pvt.) Ltd. Lahore

Project: Citi Housing Phase-I Bosan Road Multan

Our Ref. No. CL/CED/ 8608 Dated: 25-07-19

Your Ref. No. CitiHousing-Ph-I/Mul/19/01 Dated: 08-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 11-07-19 Tested on: 25-07-19 in dry/wet condition

-		Ca D	asting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
O		(9	gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(4"x8")			4.9x4.0x1.0	675	19.6	91	10400	Clad Stone
2	(12"x12")			5.8x5.8x1.0	1175	33.64	94	6260	Clad Stone
3	(18"x24")			5.8x5.8x1.3	1612	33.64	97	6460	Clad Stone
4	(12"x24")			5.9x5.7x0.7	972	33.63	95.5	6370	Clad Stone
5	(6"x24")			6.0x6.0x1.0	1288	36	97	6040	Clad Stone
End									
7									
8									
9									
10									
11									
12									
13									
14									
15									
16									

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8910

: Muhammad Qasim Bhatti (Director)

Dr. M. Yousaf

Abdullah Ibrahim Construction, Faisalabad

Project:Construction of Hussain Bibi Memorial Cardiac & General Hospital Gujranwala

Our Ref. No. CL/CED/ 8609 Dated: 25-07-19

Your Ref. No. AIC/GUJ/10 Dated: 11-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 11-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Μ	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Base. Raft Found.	5	7	2019	6x6x6	9	36	88	5480	Non Engraved
2	Base. Raft Found.	5	7	2019	6x6x6	9	36	84	5230	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8910

To: Muhammad Qasim Bhatti (Director)

Dr. M. Yousaf

Abdullah Ibrahim Construction, Faisalabad

Project:Construction of Hussain Bibi Memorial Cardiac & General Hospital Gujranwala

Our Ref. No. CL/CED/ 8610 Dated: 25-07-19

Your Ref. No. AIC/GUJ/10 Dated: 11-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 11-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Μ	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Basement Column	28	6	2019	6x6x6	9	36	90	5600	Non Engraved
2	Basement Column	28	6	2019	6x6x6	9	36	90	5600	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8914

To: Furqan Ali Malik (Chief Resident Engineer, Package-I)

Dr. M. Yousaf

CM Div., NESPAK (Pvt.) Ltd. Lahore

Project: Constt. & Rehab. of at Grade Works Along Lahore Orange Line Metro Train Corridor Pkg-1 (Sec-I) Ring Road to Daroghawala Chowk

Our Ref. No. CL/CED/ 8611 Dated: 25-07-19

Your Ref. No. 4042/13/FAM/Kerb-Stone-049 Dated: 10-07-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 11-07-19 Tested on: 25-07-19 in dry/wet condition

ö		C	astin Date*	g	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/We	et Wei	ight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		((gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Kerb Stone				6x6x6	8.4	36	119	7410	Cut Cube
2	Kerb Stone				6x6x6	8	36	130	8090	Cut Cube
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength