

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8918

Dr. M. Yousaf

To: (Engr. Muhammad Shah Zaib), Assistant Engineer

**B&W** Department UET, Lahore.

Project: Construction Site of Girls Hostel in UET, Lahore.

Our Ref. No. CL/CED/ 8612 Dated: 26-07-19

Your Ref. No. B&W/AENC/1011 Dated: 09-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//\	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Slab	4	7	2019	6Diax12	13	28.28	85	6740	Engraved
2	1st Floor Slab	4	7	2019	6Diax12	13	28.28	80	6340	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8920

To: Mr. Shaizad Munir, Resident Engineer

Dr. M. Yousaf

G3 Engineering Consultants (Pvt) Ltd. 57-M, Gulberg-III, Lahore.

Project: Consultancy Services for Design & Resident Type Supervision of the Scheme Construction of the Cantonment Board

Our Ref. No. CL/CED/ 8613 Dated: 26-07-19

Your Ref. No. G3/224/RE-37 Dated: 15-07-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-07-19 Tested on: 25-07-19 in dry/wet condition

Sr. No.	Mark*			Date* /eight	Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Column Zone 3	12	6	2019	6Diax12	14.6	28.28	88	6980	Non Engraved
2	Column Zone 3	12	6	2019	6Diax12	14	28.28	58	4600	Non Engraved
3	Column Zone 3	12	6	2019	6Diax12	13.8	28.28	55	4360	Non Engraved
End			1							
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8921

Mr. Muhammad Imtiaz, Project Manager

Dr. M. Yousaf

A.S. Enterprises Engineers & Contractors. Main Shahrah-e-Karachi.

Project: Style Textile Mill. (Contractor, M/S AS Enterprises.), (Consultant: AA Associates)

Our Ref. No. CL/CED/ 8614 Dated: 26-07-19

Your Ref. No. USD/ASE/14 Dated: 15-07-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Μ	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	C30	17	6	2019	6x6x6	9	36	122	7600	Non Engraved
2	C30	17	6	2019	6x6x6	8.4	36	133	8280	Non Engraved
3	C30	17	6	2019	6x6x6	8.6	36	120	7470	Non Engraved
4	C20	17	6	2019	6x6x6	8.9	36	97	6040	Non Engraved
5	C20	17	6	2019	6x6x6	8.4	36	89	5540	Non Engraved
6	C20	17	6	2019	6x6x6	8.4	36	94	5850	Non Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16		_								

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8945

Го: Hafiz Mahmood UI Hassan, General Manager

Dr. M. Yousaf

D-Mix Concrete Products. PHA Phase-9, Lahore Cantt. Project: Doctor Muhammad Ali Memorial Hospital.

Our Ref. No. CL/CED/ 8615 Dated: 26-07-19

Your Ref. No. Nil Dated: 17-07-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-07-19 Tested on: 25-07-19 in dry/wet condition

Sr. No.	Mo-l-*			Date*	Size	Weight	Area of X-	Ultimate	Ultimate	Domestra
Sr. I	Mark*	/۷۷	et vv	eight 'eight	(in)	(lbs./gms)	Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Slab	10	7	2019	6Diax12	13	28.28	45	3570	Non Engraved
2	Slab	10	7	2019	6Diax12	14	28.28	53	4200	Non Engraved
End			-							
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8977 & 8991 Dr. M. Yousaf

Mr. Atta Muhammad, Civil Engineer

Bullehshah Packaging (Pvt) Ltd. Kasur.

Project: Nil

Our Ref. No. CL/CED/ 8616-1 of 2 Dated: 26-07-19

Your Ref. No. Nil Dated: 22-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
(i)			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1		2	6	2019	6x6x6	8.4	36	60	3740	Engraved
2		2	6	2019	6x6x6	8.6	36	53	3300	Engraved
3		3	6	2019	6x6x6	8.6	36	48	2990	Engraved
4		23	6	2019	6x6x6	8.4	36	53	3300	Engraved
5		23	6	2019	6x6x6	8.4	36	56	3490	Engraved
End										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8977 & 8991

Mr. Atta Muhammad, Civil Engineer Bullehshah Packaging (Pvt) Ltd. Kasur. Dr. M. Yousaf

Project: Nil

Our Ref. No. CL/CED/ 8616-2 of 2 Dated: 26-07-19

Your Ref. No. Nil Dated: 22-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-07-19 Tested on: 25-07-19 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et W	eight 'eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1		29	5	2019	6Diax12	13.8	28.28	38	3010	Non Engraved
2		29	5	2019	6Diax12	14	28.28	48	3810	Non Engraved
3		29	5	2019	6Diax12	14	28.28	47	3730	Non Engraved
4		29	5	2019	6Diax12	14	28.28	48	3810	Non Engraved
End										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8933

To: Furqan Ali Malik (Chief Resident Engineer, Package-I)

CM Div., NESPAK (Pvt.) Ltd. Lahore. (M/s Kamal Developers)

Dr. M. Yousaf

Project:Constt. & Rehab. of at Grade Works Along Lahore Orange Line Metro Train Corridor Pkg-1 (Sec-II) from Coop Store to Bohar Wala Chowk.

Our Ref. No. CL/CED/ 8617 Dated: 26-07-19

Your Ref. No. 4042/13/FAM/Kerb-Stone-012 Dated: 01-07-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-07-19 Tested on: 25-07-19 in dry/wet condition

٠		[	astin Date	*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*		/Wet Veigh		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(	(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Kerb Stone				6x5.9x5.4	8	35.4	133	8420	Cut Cube
End										
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8937

Го: Muhammad Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg-II, Lahore

Project: Construction of P-156 Gulberg-II Lahore.

Our Ref. No. CL/CED/ 8618 Dated: 26-07-19

Your Ref. No. P-156-012 Dated: 16-07-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-07-19 Tested on: 25-07-19 in dry/wet condition

				D - 1 - *	0:	M/ -! - 1 (	A	1.110	1.110 (	
		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	51 (4000 Psi)	12	7	2019	6Diax12	13.4	28.28	45	3570	Non Engraved
2	52 (4000 Psi)	12	7	2019	6Diax12	13.6	28.28	50	3970	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15								_		
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8955

To: Muhammad Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg-II, Lahore

Project: Construction of P-156 Gulberg-II Lahore.

Our Ref. No. CL/CED/ 8619 Dated: 26-07-19

Your Ref. No. P-156-014 Dated: 19-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-07-19 Tested on: 25-07-19 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	et W	eight /	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	9 (4000 Psi)	24	6	2019	6Diax12	14.2	28.28	73	5790	Non Engraved
2	10 (4000 Psi)	24	6	2019	6Diax12	14.4	28.28	77	6100	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										_
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8956

To: Muhammad Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg-II, Lahore

Project: Construction of P-156 Gulberg-II Lahore.

Our Ref. No. CL/CED/ 8620 Dated: 26-07-19

Your Ref. No. P-156-015 Dated: 19-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-07-19 Tested on: 25-07-19 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	et W	eight/	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	55 (4000 Psi)	14	7	2019	6Diax12	14	28.28	48	3810	Non Engraved
2	56 (4000 Psi)	14	7	2019	6Diax12	14	28.28	50	3970	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

 $Results\ can\ also\ be\ seen\ on\ website\ \underline{http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports\&id=6}$ 

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



To:

# Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8943

Arfan ul Haq,RE,NESPAK Pvt. Ltd.Highways and Transportation Enggg. Section, Islamabad.

Dr. M. Yousaf

Kerb Stone, Manufactured by Universal Cotex at RD 42+00 Project:(CPEC),West. Route Hakla (on M1)~Yarak(D.I.Khan) Motorway,Pack.-3(Tarap to Kot Balian)

Our Ref. No. CL/CED/ 8621 Dated: 26-07-19

Your Ref. No. CPEC/NESPAK/PKG3/19/1035 Dated: 04-07-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-07-19 Tested on: 25-07-19 in dry/wet condition

Sr. No.	Mark*		ting Da		Size	Weight	Area of X-	Ultimate load	Ultimate Stress	Remarks
Sr.	Wark	///	ervvei	gnı	(in)	(lbs./gms)	Section	1080	Suess	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Kerb Stone				6x6x6	8.2	36	90	5600	Cut Cube
2	Kerb Stone				6x6x6	8	36	52	3240	Cut Cube
3	Kerb Stone				6x6x6	8	36	65	4050	Cut Cube
End			1	1						
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8963

To: Ibna Al Aziz Dr. M. Yousaf

117 Ahmad Block, New Garden Town, Lahore.

Project: Fuad Sb Home 5 Marla House at Upper Mall Lahore.

Our Ref. No. CL/CED/ 8622 Dated: 26-07-19

Your Ref. No. Nil Dated: 22-07-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//\	et W	eight/	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1		31	5	2019	6Diax12	13	28.28	60	4760	Non Engraved
2		31	5	2019	6Diax12	13	28.28	57	4520	Non Engraved
3		31	5	2019	6Diax12	13	28.28	39	3090	Non Engraved
4		31	5	2019	6Diax12	13	28.28	32	2540	Non Engraved
End										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8964

To: Ibna Al Aziz Dr. M. Yousaf

117 Ahmad Block, New Garden Town, Lahore.

Project: Fuad Sb Home 5 Marla House at Upper Mall Lahore.

Our Ref. No. CL/CED/ 8623 Dated: 26-07-19

Your Ref. No. Nil Dated: 22-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-07-19 Tested on: 25-07-19 in dry/wet condition

		Coating Data*			Cizo	Weight	Aron of	I litim at a	I Iltim ot a	
	Mark*	Casting Date* /Wet Weight (gms)			Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
							(Sq. in)	(Tons/lbs)	(Psi)	
1		15	5	2019	6x6x6	8	36	53	3300	Non Engraved
2		15	5	2019	6x6x6	8	36	55	3430	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8946

To: Mr. Ali Safdar, Site Engineer

Dr. M. Yousaf

Shelter Associates, Lahore Cantt. (M/s Asfar Builder-Lahore).

Project: House No. 232-233/C, TECH Society Lahore.

Our Ref. No. CL/CED/ 8624 Dated: 26-07-19

Your Ref. No. Gen/19/54 Dated: 17-07-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-07-19 Tested on: 25-07-19 in dry/wet condition

o 9	Made			Date*	Size	Weight	Area of X-	Ultimate	Ultimate	Daniela
Sr. No.	Mark*	/V\	et v	eight/	(in)	(lbs./gms)	Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Pool Bed	13	6	2019	6x6x6	8.4	36	70	4360	Non Engraved
2	Pool Bed	13	6	2019	6x6x6	8.4	36	65	4050	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8949

To: Sub Divisional Officer

Dr. M. Yousaf

**Buildings Sub Division No.15, Lahore.** 

Project: Construction of New Administration Block in the Premises of Lahore High Court Lahore.

Our Ref. No. CL/CED/ 8625 Dated: 26-07-19

Your Ref. No. 2376 Dated: 17-07-19

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-07-19 Tested on: 25-07-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Pile Work	3	7	2019	6x6x6	9	36	101	6290	Non Engraved
2	Pile Work	3	7	2019	6x6x6	9	36	110	6850	Non Engraved
3	Pile Work	3	7	2019	6x6x6	9	36	117	7280	Non Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8950

o: (Engr. Muhammad Nayab Khalid) Planning and Monitoring Engineer

Dr. M. Yousaf

Matrix Management (Pvt) Ltd. 116 C Model Town, Lahore.

Project: Construction of Ibraheem Industries, Lahore.

Our Ref. No. CL/CED/ 8626 Dated: 26-07-19

Your Ref. No. MW/MMPL-1/2019/11 Dated: 18-07-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-07-19 Tested on: 25-07-19 in dry/wet condition

	Mark*	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1		3	7	2019	6Diax12	13.4	28.28	75	5950	Engraved
2		3	7	2019	6Diax12	13.2	28.28	73	5790	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8954

Го: Mr. Irfan Haider, Project Manager

Dr. M. Yousaf

**Roots International Schools.** 

Project: Roots International School Palm Tree Campus Sialkot.

Our Ref. No. CL/CED/ 8627 Dated: 26-07-19

Your Ref. No. RIS/SB/SKT15072019 Dated: 15-07-19

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-07-19 Tested on: 25-07-19 in dry/wet condition

	Mark*	Casting Date* /Wet Weight			Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1		7	7	2019	6Diax12	14	28.28	38	3010	Non Engraved
2		7	7	2019	6Diax12	14	28.28	33	2620	Non Engraved
End			-							
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength