

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

8729 Dr. Umbreen

Buildings Sub Division Shakargarh.

Project: Construction of Dangerous School in Govt. I T High School Shakargarh Distt. Narowal.

Our Ref. No. CL/CED/	8313	Dated:	13-06-19
Your Ref. No.	1519/Sg	Dated:	09-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

31-05-19 Tested on:

12-06-19 in dry/wet condition

ir					I					
_		Casting		Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:2:4)	10	4	2019	6x6x6	8.4	36	102	6350	Non Engraved
2	(1:2:4)	10	4	2019	6x6x6	8.3	36	96	5980	Non Engraved
3	(1:2:4)	10	4	2019	6x6x6	8	36	94	5850	Non Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Imran Akhtar, Project Manager CM Engineering (Pvt) Ltd. Project: CMPAK, Site ID-42561

8728 Dr. Umbreen

Our Ref. No. CL/CED/	8314	Dated:	13-06-19
Your Ref. No.	CME/Cubes/CMPAK/506	Dated:	27-05-19

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

31-05-19

12-06-19 in dry/wet condition

Sr. No.	Mark*		Casting Date* /Wet Weight (gms)		Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Pier Foundation	20	(gii	2019	6x6x6	8.4	36	100	6230	Non Engraved
2	Pier Foundation	20	5	2019	6x6x6	8.4	36	102	6350	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Imran Akhtar, Project Manager To: CM Engineering (Pvt) Ltd. Project: CMPAK, Site ID-42622

8728 Dr. Umbreen

Our Ref. No. CL/CE	D/	8315	Dated:	13-06-19
Your Ref. No.	CME/Cubes	s/CMPAK/507	Dated:	30-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

31-05-19 Tested on:

12-06-19 in dry/wet condition

		1								
		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//	Vet W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(grr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column	2	5	2019	6x6x6	8.2	36	106	6600	Non Engraved
2	Column	2	5	2019	6x6x6	8.4	36	104	6480	Non Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

8750 Dr. Umbreen

To: (Aamir Shehzad Mughal), Site Engineer Dr. U BKRY Lahore. Dr. U Dr. U

Project:Constt.of BKRY 30-Km Ferozpur Road Lhr.(Ground & Mazzanine F.Slab & Beams Block"B")

Our Ref. No. CL/CED/	8316	Dated:	13-06-19
Your Ref. No.	TBL/19/012	Dated:	12-06-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-06-19

Tested on:

12-06-19 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*		et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	M.F Slab & Beams	13	5	2019	6Diax12	14	28.28	53	4200	Non Engraved
2	M.F Slab & Beams	13	5	2019	6Diax12	14.2	28.28	51	4040	Non Engraved
3	M.F Slab & Beams	13	5	2019	6Diax12	13.4	28.28	43	3410	Non Engraved
4	G.F Slab & Beams	1	6	2019	6Diax12	13.8	28.28	33	2620	Non Engraved
5	G.F Slab & Beams	1	6	2019	6Diax12	14	28.28	39	3090	Non Engraved
6	G.F Slab & Beams	1	6	2019	6Diax12	14	28.28	37	2940	Non Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (QCD)

8595 Engr. Aamina

WASA LDA Lahore. (M/S H&M Enterprises)

Project:Ten.No.XEN/O&M-II/RT/86/979-84,12-03-2019.Improv.of Sewrg.Sys.at St.No.13 Khow Wali

Our Ref. No. CL/CED/	8317	Dated:	13-06-19
Your Ref. No.	QCD/346-47	Dated:	30-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

07-05-19 Tested on:

11-06-19 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/Wet Weight		(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	101			3852	9.2x4.4x2.9	3505	40.48	39	2160	9
2	101			4061	9.1x4.5x3.1	3824	40.95	39	2140	5.83
3	101			4070	9.2x4.6x3.1	3803	42.32	33	1750	6.56
4	101			3554	9.1x4.5x2.9	3252	40.95	36	1970	8.49
5	101			3657	9x4.4x2.9	3453	39.6	35	1980	5.57
6	101			3899	9.3x4.3x3.0	3390	39.99	41	2300	13.05
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to

be interpreted in the light of above factors by the engineer.

supervisor(lab)



Our Rof No

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Deputy Director (QCD)

8595 Engr. Aamina

WASA LDA Lahore. (M/S H&M Enterprises) Project:Ten.No.XEN/O&M-III/RT/136/Saving Funds/City/2018-19/1876-80, 27-03-2019.Repair of Surface Drain

CL/CED/	8318	Dated:	13-06-19
Your Ref. No.	QCD/355-56	Dated:	30-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

07-05-19

Specimens received on:

Tested on:

11-06-19 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X-	Ultimate load	Ultimate Stress	Remarks
ي. ۲.		-			(11)	(103./9113)	Section			Remarks
			(gm	S)			(Sq. in)	(Tons/lbs)	(Psi)	
1	101			4076	9.2x4.4x2.9	3651	40.48	44	2440	10.4
2	101			3691	8.9x4.5x3.0	3387	40.05	35	1960	8.23
3	101			3600	8.9x4.5x2.9	3277	35.6	41	2580	8.97
4	101			3741	9.1x4.5x2.9	3388	40.95	37	2030	9.43
5	101			3989	9.2x4.5x3.0	3650	41.4	25	1360	8.49
6	101			3845	9.1x4.4x3.1	3455	40.04	47	2630	10.14
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: (Zulfigar H Butt), CEO

8716 Dr. Umbreen

Al-Tawakkal Construction Company. 7-Edgerton Road, Lahore. Project: Boundary Wall at PSO Depot, Chakpirana.

Our Ref. No. CL/CED/	8319	Dated:	13-06-19
Your Ref. No.	TCC/19/42	Dated:	30-05-19

COMPRESSION TEST REPORT

Tested on:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

30-05-19

12-06-19 in dry/wet condition

								1		I
Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1	B.W. Foundation	24	5	2019	6x6x6	8.4	36	98	6100	Engraved
2	B.W. Foundation	24	5	2019	6x6x6	8.4	36	90	5600	Engraved
End										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: (Engr. Roshaan Bin Naghman) Assistant Director (Civil), O i/c RMTL. Civil Aviation Authority, Allama Iqbal International Airport Lahore. Project: Improvement/Rehabilitation of Secondary Runway at AIIAP, Lahore. 8695 Dr. Umbreen

Our Ref. No. CL/CED/ 8320 Dated: 13-06-19 AIIAP/1656-Your Ref. No. 01/045/LACV/II/539 Dated: 15-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

24-05-19

Tested on:

12-06-19 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		٨	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		13 3 2019		6x6x6	7.8	36	79	4920	Non Engraved	
2		13	3	2019	6x6x6	8.2	36	55	3430	Non Engraved
3		14	3	2019	6x6x6	8.4	36	59	3680	Non Engraved
4		14	3	2019	6x6x6	8.4	36	61	3800	Non Engraved
5		16	3	2019	6x6x6	8	36	88	5480	Non Engraved
6		16	3	2019	6x6x6	8.2	36	69	4300	Non Engraved
7		18	3	2019	6x6x6	8	36	43	2680	Engraved
8		18	3	2019	6x6x6	8	36	73	4550	Engraved
9		21	3	2019	6x6x6	8	36	57	3550	Engraved
10		21	3	2019	6x6x6	7.8	36	59	3680	Engraved
11		22	3	2019	6x6x6	8	36	55	3430	Engraved
12		22	3	2019	6x6x6	8	36	55	3430	Engraved
13		23	3	2019	6x6x6	8	36	55	3430	Engraved
14		23	3	2019	6x6x6	8	36	55	3430	Engraved
End										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)