

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Arfan Nazir, Manager Civil

8667 Engr. Aamina

Nishat Mills Ltd. (Contractor: Guarantee Engineers (Pvt) Ltd.) Project: Nishat 3.2 MW Power Plant Extension Unit 42. (TG Foundation & Column Footing).

Our Ref. No. CL/CED/	8242	Dated:	28-05-19
Your Ref. No.	Nil	Dated:	20-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

21-05-19 Tested on:

21-05-19 in dry/wet condition

						1				
_		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et W	eight/	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	C-35	13	5	2019	6Diax12	14	28.28	57	4520	Engraved
2	C-35	13	5	2019	6Diax12	14	28.28	55	4360	Engraved
3	C-35	13	5	2019	6Diax12	13.8	28.28	59	4680	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Muhammad Saleem Bhatti, Resident Engineer AZ Engineering Associates.

Project:Const.of Road K.L.Warraich Rigid Pavem. Dual Carriageway GWA to HFZ,L=2.00 Km (Group-2)

Our Ref. No. CL/CED/	8243	Dated:	28-05-19
Your Ref. No.	AZEA/REKMK/800	Dated:	20-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

24-05-19

Tested on: 2

28-05-19 in dry/wet condition

		Casting Dat		Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	114+20-115+10	23	4	2019	6x6x6	8.4	36	79	4920	Non Engraved
2	114+20-115+10	23	4	2019	6x6x6	8.4	36	102	6350	Non Engraved
3	114+20-115+10	23	4	2019	6x6x6	8.2	36	114	7100	Non Engraved
4	112+40-114+20	24	4	2019	6x6x6	8.2	36	104	6480	Non Engraved
5	112+40-114+20	24	4	2019	6x6x6	8.2	36	86	5360	Non Engraved
6	112+40-114+20	24	4	2019	6x6x6	8.4	36	104	6480	Non Engraved
End										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

8691 Dr. Rizwan Azam



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Resident Engineer

8623 Dr. Rizwan Azam

KQC Road Project N-25. (Izhar Pvt. Ltd.) Project: Kuchlak Bypass Additional Work under USAID for Kalat-Quetta-Chaman Section N-25.

Our Ref. No. CL/CED/	8244	Dated:	28-05-19
Your Ref. No.	KQC/Add/RE/275	Dated:	04-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

14-05-19 Tested on:

28-05-19 in dry/wet condition

Casting Size Weight Area of Ultimate Ultimate Date* o Z Х-Wet Mark* (in) (lbs./gms) load Stress Remarks Weight Section ັດ (Tons/lbs) (gms) (Sq. in) (Psi) 1 Kerb Stone 6x6x5.4 7795 36 104 6480 Cut Cube End ------------------------------3 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

Divisional Forest Officer To:

8696 Dr. Rizwan Azam

Okara Forest Division Okara. (M/S Manzoor Aalam & Sons) Project: Segment used for Lining in Depalpur Plantation, Piplipahar District Okara.

Tested on:

Our Ref. No. CL/CED/	8245	Dated:	28-05-19
Your Ref. No.	4746/AC Okara	Dated:	12-04-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

27-05-19

28-05-19 in dry/wet condition

		Cas		J Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	N	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(grr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Segment # 7	10	3	2019	6x6x6	8.4	36	134	8340	Engraved
2	Segment # 8	11	3	2019	6x6x6	8.3	36	134	8340	Engraved
3	Segment # 9	23	3	2019	6x6x6	8.2	36	138	8590	Engraved
End										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Hassan Ali, Director Projects

8671 Dr. M. Yousaf

Filigree Enterprises, Temple Road, Lahore. (Client: Spark World Electronics (Pvt) Ltd.) **Project: Boundary Wall**

Tested on:

Our Ref. No. CL/CED/	8246	Dated:	28-05-19
Your Ref. No.	Nil	Dated:	21-05-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

22-05-19

22-05-19 in dry/wet condition

Ġ		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Col. Line 14,15	13	5	2019	6x6x6	8.4	36	60	3740	Non Engraved
2	Col. Line 14,15	13	5	2019	6x6x6	8.4	36	104	6480	Non Engraved
3	Col. Line 12C	20	4	2019	6x6x6	8.4	36	86	5360	Non Engraved
4	Col. Line 12C	20	4	2019	6x6x6	8.4	36	48	2990	Non Engraved
End										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)