

University of Engineering and Technology, Lahore Phone Nos. 042-99029202. 042-99029217

9409

Dr. Aqsa

To: (Ch. Liaqat Ali), Resident Engineer

G3 Engineering Consultant (Pvt) Ltd. Project: Consultancy Services for Resident Construction Supervision of Provision of Missing Specialties

for Up Gradation of DHQ Hospital to Teaching Hospital Gujranwala. (Group 1).

Our Ref. No. CL/CED/ 9269 Dated: 19-11-19

Your Ref. No. G3/205/1123 Dated: 21-10-19

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28-10-19 Tested on: 12-11-19 in dry/wet condition

h		I		T		1	1	
		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	S		8.8x4.4x2.9	3095	38.72	22	1280	
2	S		8.8x4.4x2.9	3110	38.72	63	3650	
3	S		8.8x4.3x2.8	3019	38.72	31	1800	
4	S		8.8x4.3x2.9	3041	37.84	67	3970	
5	S		8.8x4.4x2.8	3071	38.72	33	1910	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9409

To: (Ch. Liaqat Ali), Resident Engineer

Dr. Aqsa

G3 Engineering Consultant (Pvt) Ltd.

Project: Consultancy Services for Resident Construction Supervision of Provision of Missing Specialties for Up Gradation of DHQ Hospital to Teaching Hospital Gujranwala. (Group 1).

Our Ref. No. CL/CED/ 9270 Dated: 19-11-19

Your Ref. No. G3/205/1126 Dated: 21-10-19

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28-10-19 Tested on: 12-11-19 in dry/wet condition

Sr. No.	Mark*	Casting Date* Wet Weight (gms)	Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	H	(91113)	8.9x4.4x2.9	3124	39.16	38	2180	
1								
2	Н		8.9x4.4x2.8	3147	39.16	32	1830	
3	Н		8.9x4.3x2.9	3123	38.27	36	2110	
4	Н		8.9x4.4x2.9	3169	39.16	32	1830	
5	Н		9.0x4.4x2.9	3094	39.6	46	2610	
6	Н		9.0x4.4x2.9	3106	39.6	49	2780	
7	Н		8.9x4.3x2.9	3129	38.27	42	2460	
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

**Director/Dy. Director Concrete Laboratory** 

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9418

To: (Engr. Muhammad Abdullah), Assistant Engineer

Dr. Aqsa

**B&W Department UET, Lahore.** 

Project: Construction Site of Workshop and Design Center in UET, Lahore.

Our Ref. No. CL/CED/ 9271 Dated: 19-11-19

Your Ref. No. B&W/AEN/1171 Dated: 29-10-19

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29-10-19 Tested on: 12-11-19 in dry/wet condition

		Casting	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Date* /Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RB		9.0x4.4x2.9	2719	39.6	75	4250	
2	RB		8.9x4.4x2.9	2829	39.16	25	1430	
3	RB		8.9x4.3x3.0	2831	38.27	52	3050	
4	RB		8.9x4.4x3.0	2784	39.16	39	2240	
5	RB		9.0x4.4x3.0	2841	39.6	49	2780	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9418

Dr. Aqsa

To: (Engr. Muhammad Abdullah), Assistant Engineer

**B&W** Department UET, Lahore.

Project: Construction Site of Workshop and Design Center in UET, Lahore.

Our Ref. No. CL/CED/ 9272 Dated: 19-11-19

Your Ref. No. B&W/AEN/1170 Dated: 29-10-19

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29-10-19 Tested on: 12-11-19 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RB		8.8x4.3x3.0	2790	37.84			
2	RB		9.0x4.4x3.0	2809	39.6			
3	RB		8.9x4.3x2.9	2751	38.27			
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength