

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9222

Dr. Aqsa

To: Engr. Imran Zahid, A. Senior Engineer

University of Education, Lahore. (M/s WEBOG Global).

Project: Construction of Warden House at UE Township Campus.

Our Ref. No. CL/CED/ 8948 Dated: 26-09-19

Your Ref. No. UE/Engg/UE/2019/549 Dated: 17-09-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 23-09-19 Tested on: 24-09-19 in dry/wet condition

	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.		M	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks	
0)			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)		
1	F.F. Slab	15	8	2019	6x6x6	7.8	36	74	4610	Non Engraved	
2	F.F. Slab	15	8	2019	6x6x6	8.8	36	106	6600	Non Engraved	
3	F.F. Slab	15	8	2019	6x6x6	8.6	36	100	6230	Non Engraved	
4											
5											
6											
7											
8											
9											
10											
11											
12											
13											
14											
15											
16											

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9222

Dr. Aqsa

To: Engr. Imran Zahid, A. Senior Engineer

University of Education, Lahore. (M/s WEBOG Global).

Project: Construction of Warden House at UE Township Campus.

Our Ref. No. CL/CED/ 8949 Dated: 26-09-19

Your Ref. No. UE/Engg/UE/2019/548 Dated: 17-09-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 23-09-19 Tested on: 24-09-19 in dry/wet condition

	Mark*	Casting Date* //Wet Weight			Size	Weight	Area of Ultimate Ul	Ultimate		
Sr. No.					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	G.F. Slab	5	5 8 2019		6x6x6	8.8	36	92	5730	Non Engraved
2	G.F. Slab	5	8	2019	6x6x6	8.4	36	73	4550	Non Engraved
3	G.F. Slab	5	8	2019	6x6x6	8	36	112	6970	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9166

To: Hamza Raees. Chief Executive.

Dr. Umbreen

Livewell Capsules Pvt. Ltd. 107, Sundar Industrial Estate, Raiwind Road, Lahore. Project: Construction of Livewell Capsule Plot No.107, Sundar Industrial Estate Lahore.

Our Ref. No. CL/CED/ 8950 Dated: 26-09-19

Your Ref. No. Nil Dated: 04-09-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-09-19 Tested on: 26-09-19 in dry/wet condition

	Mark*	Casting Date* /Wet Weight			Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	G.F Column, F1/D	20	6	2019	6Diax12	14	28.28	91	7100	Non Engraved
2	G.F Column, F1/D	20	6	2019	6Diax12	14.2	28.28	84	6550	Non Engraved
3	F.F Column F2/E	18	7	2019	6Diax12	13.4	28.28	88	6860	Non Engraved
4	F.F Column F2/E	18	7	2019	6Diax12	13.8	28.28	72	5620	Non Engraved
5	G.F Slab A-D/1-3	17	7	2019	6Diax12	14.6	28.28	75	5850	Non Engraved
6	G.F Slab A-D/1-3	17	7	2019	6Diax12	14.4	28.28	87	6780	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9205

To: (Tasawar Riaz), Director

Dr. Umbreen

Multi Line Engineers.

Project: Construction of Miscellaneous at Unilever Pakistan Foods Ltd.

Our Ref. No. CL/CED/ 8951 Dated: 26-09-19

Your Ref. No. Nil Dated: 19-09-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-09-19 Tested on: 26-09-19 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1	(A1,A2), Noodle 1200, Col. Found	8	9	2019	6Diax12	13	28.28	27	2110	Non Engraved
2	(A1,A2), Noodle 1200, Col. Found	8	9	2019	6Diax12	13	28.28	30	2340	Non Engraved
3	(B1,B2), Dispatch Room, Col. Found	11	9	2019	6Diax12	13.4	28.28	41	3200	Non Engraved
4	(B1,B2), Dispatch Room, Col. Found	11	9	2019	6Diax12	13.2	28.28	42	3280	Non Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15	-									
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength