

Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, M/S RTCC Pvt Ltd Lahore

Reference # CED/TFL **34187** (Dr. Ali Ahmed)

Reference of the request letter # Nil

Dated: 15-11-2019

Dated: 15-11-2019

Tension Test Report (Page – 1/1)

Date of Test 19-11-2019 Gauge length 2 inches

Description Aluminum Pipe & Plate Strip Tensile Test

Sr. No.	Designation	Size of Strip	Size of Strip X Section Area Yield load		Breaking Load	Breaking Load Yield Stress		Elongation	% Elongation	Remarks		
	(mm)	(mm)	(mm^2)	(kg)	(kg)	(MPa)	(MPa)	(in)				
1	Pipe 4mm Thickness	27.40x3.45	94.53	2040	2600	211.70	269.82	0.25	12.50			
2		27.40x3.45	94.53	2170	2500	225.20	259.44	0.20	10.00			
3	D. 5 5111	27.60x4.90	135.24	2481	2900	179.97	210.36	0.40	20.00			
4	Pipe 5mm Thickness	27.60x4.90	135.24	2440	2800	176.99	203.11	0.40	20.00			
5	Plate 20mm	27.60x20.20	557.52	16540	18300	291.03	322.00	0.50	25.00			
6	Thickness	27.60x20.20	557.52	15630	18400	275.02	323.76	0.40	20.00			
		0	nly Six S	amples for	Tensile '	Test		1				
	Bend Test											

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To,
Assistant Engineer (Civil)
University of Okara
(Construction of University Service Club at University of Okara)

Reference # CED/TFL **34189** (Dr. Ali Ahmed)

Reference of the request letter # Nil

Dated: 18-11-2019

Dated: 18-11-2019

Tension Test Report (Page -1/1)

Date of Test 19-11-2019 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/		Area (in²)		Yield load	Breaking Load	Yield Stress (psi)			e Stress si)	Elongation	Elongation	Remarks
S	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	% E	R
1	0.383	3	0.379	0.11	0.113	4000	5100	80200	78270	102200	99800	1.10	13.8	
•	-	-	•	1	-	•	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	•	-	•	-	-	-	-	-	-	-	
-	•	•	•	•	-	•	-	-	-	-	-	-	-	
		•	•	•	-	•	-	-	-	-	-	-	-	
			N	ote: on	ly one s	sample fo	or tensile	and one	sample f	or bend t	est	1	Ī	
#2	Bend Test #3 Bar Bend Test Through 180° is Satisfactory													
#3	Bar Ben	d Test	Through	180° is	s Satisfa	ectory								

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, Assistant Engineer (Civil) University of Okara

(Finishing and External Development of Student Shoping Center at University of Okara)

Reference # CED/TFL **34190** (Dr. Ali Ahmed)

Reference of the request letter # Nil

Dated: 18-11-2019

Dated: 18-11-2019

Tension Test Report (Page -1/1)

Date of Test 19-11-2019 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	M Diameter/ size		Area (in²)		Yield load	Breaking Load	Yield Stress (psi)			e Stress si)	Elongation	Elongation	Remarks
S	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	% F	Re
1	0.388	3	0.381	0.11	0.114	4000	5200	80200	77320	104200	100600	1.10	13.8	
-	•	•	-	1	-	-	-	•	-	-	•	-	-	
-	•	ı	-	1	-	-	-	•	-	-	•	-	-	
-	-	-	-	•	-	-	-	-	-	-	•	-	-	
1	•	•	-	•	-	-	-	•	-	-	•	-	-	
-		-	-	-	-	-	-	-	-	-	-	-	-	
			N	ote: on	ly one s	sample fo	r tensile	and one	sample f	or bend t	est	1		
#2	Bend Test													
#3	#3 Bar Bend Test Through 180° is Satisfactory													

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, Deputy Director (QCD) WASA, LDA, Lahore

(Manufacturing of R.C.C Manhole Covers in Different Sizes)(M/s Akram Pipes)

Reference # CED/TFL **34191** (Dr. Ali Ahmed)

Reference of the request letter # QCD/1495-96

Dated: 18-11-2019

Dated: 13-11-2019

Tension Test Report (Page – 1/2)

Date of Test 19-11-2019 Gauge length 2 inches

Description Angle Iron Strip Tensile and Bend Test

Sr. No.	Designation	Size of Strip	X Section Area	Yield load	Breaking Load	Yield Stress	Ultimate Stress	Elongation	· Elongation	Remarks
	(inch)	(mm)	(mm^2)	(kg)	(kg)	(MPa)	(MPa)	(in)	%	
1	2x2x1/4	23.95x6.75	161.66	5800	9000	351.96	546.14	0.50	25.00	
2	2x2x1/4	23.95x6.75	161.66	6200	9300	376.23	564.34	0.50	25.00	
-		-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	
-		-	-	-	-	-	-	-	-	
		Only Two Sa	mples for	Tensile :	and One s	ample fo	r Bend T	Cest	1	
					T					

Bend Test

Strip Taken from Angle Iron (2"x2"x1/4") Bend Test Through 180° is Satisfactory

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, Deputy Director (QCD) WASA, LDA, Lahore

(Manufacturing of R.C.C Manhole Covers in Different Sizes)(M/s Akram Pipes)

Reference # CED/TFL **34191** (Dr. Ali Ahmed) Reference of the request letter # QCD/1495-96

Weight &Size Test Report (Page – 2/2)

Date of Test 19-11-2019

Gauge length -----

Description Angle Iron Weight and Size Test

Sr. No.	Designation	Weight	Length	Weight per Unit Length	L-1	L-2	Thickness	Remark
	(inch)	(g)	(cm)	(kg/m)	(mm)	(mm)	(mm)	
1	2x2x1/4	3024	61.00	4.96	52.00	52.10	6.50	
-	-	-	-	-	ı	1	-	
-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	
			Only One	Sample fo	r Test			

I/C Testing Laboratoires UET Lahore, Pakistan.

Dated: 18-11-2019

Dated: 13-11-2019

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To,

Resident Engineer

G3 Engineering Consultant (Pvt) Ltd

Consultancy Services for Resident Construction Supervision of Provision of Construction of Infrastructure and Allied Works at Rachna Industrial Parks at District Sheikhupura. Phase-II

Reference # CED/TFL **34196** (Dr. Ali Ahmed)

Reference of the request letter # G-3/0207/1098

Dated: 18-11-2019

Dated: 15-11-2019

Tension Test Report (Page -1/1)

Date of Test 19-11-2019 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	M Diameter/ size		Area (in²)		Yield load	Breaking Load	Yield Stress (psi)			e Stress si)	Elongation	Elongation	Remarks
S	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	% E	Re
1	0.362	3	0.368	0.11	0.106	3300	5300	66200	68430	106200	109900	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-		-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
			N	ote: on	ly one s	sample fo	r tensile	and one	sample f	or bend t	est			
	Bend Test													
#3	#3 Bar Bend Test Through 180° is Satisfactory													

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples

AHOTE

STRUCTURAL ENGINEERING DIVISION

Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, Resident Engineer NESPAK

Development of Infrastructure in LDA City, Lahore (Package 2 of Development Area – 1) (Kamran Steel)

Reference # CED/TFL **34198** (Dr. Ali Ahmed) Dated: 18-11-2019

Reference of the request letter # 4047/13/OH/03-MBCC/28 Dated: 12-11-2019

Tension Test Report (Page -1/1)

Date of Test 19-11-2019 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/		Area (in²)		Yield load Breaking Load		Yield Stress (psi)		Ultimate Stress (psi)		Elongation	Elongation	Remarks
S	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	H %	R
1	4.203	10	1.254	1.27	1.235	39200	54600	68100	69950	94800	97500	1.30	16.3	
2	4.188	10	1.252	1.27	1.231	34800	51200	60400	62310	88900	91700	1.30	16.3	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
			No	ote: onl	ly two s	amples f	or tensile	and one	sample f	or bend	test	1		
							D 17							
Д10) D P	1 T. ·	.Tl	1. 1000	:- 0-4' 4	C4	Bend T	est						
#1() Bar Be	nd Test	Throug	gn 180°	is Satisi	ractory								

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples