

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10087

To: Arsalan Arshad, Project Manager

Dr. Umbreen

M/s DEPAC, Lahore.

Project: Construction of 4-Storied Building DR. Maqbool Ahmad Block at KEMU Lahore.

Our Ref. No. CL/CED/ 48 Dated: 27-04-20

Your Ref. No. T-29/20/03 Dated: 12-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 22-04-20 in dry/wet condition

		Са	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Grid 3rd F. Slab (A- F/8-14)	6	3	2020	6Diax12	13.8	28.28	59	4680	Engraved
2										
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10085

To: M. Sohail Anjum, Project Manager

Dr. M. Yousaf

Multistory Offices, P-156 Gulberg II, Lahore.

Project: Construction of P-156 Gulberg-II, Lahore.

Our Ref. No. CL/CED/ 49 Dated: 27-04-20

Your Ref. No. P-156-097 Dated: 12-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 23-04-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	(347) 3000 Psi	12	2	2020	6Diax12	14.1	28.28	78	6180	Non Engraved
2	(348) 3000 Psi	12	2	2020	6Diax12	14.2	28.28	81	6420	Non Engraved
3	(349) 3000 Psi	12	2	2020	6Diax12	14	28.28	77	6100	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength