

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10086

To: Yasir Mahmud, CEO YASCON

Dr. M. Yousaf

Yascon Center, Chenab Rangers Road, Opposite Kent Housing, Sialkot. Project: Garrison Academy 204 Bridge Co Gwa Cantt (RD Office Gwa Cantt).

Our Ref. No. CL/CED/ 50 Dated: 28-04-20

Your Ref. No. YAS/UET/08/11 Dated: 06-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 23-04-20 in dry/wet condition

Sr. No.	Mark*		et V	Date*	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load (Tons/lbs)	Ultimate Stress	Remarks
	DOO Farry dation	44	(gn		CD:40	40.0	(Sq. in)		(Psi)	Non Engage
1	RCC Foundation	11	2	2020	6Diax12	13.2	28.28	25	1980	Non Engraved
2	RCC Foundation	11	2	2020	6Diax12	13	28.28	22	1750	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10086

To: Yasir Mahmud, CEO YASCON

Dr. M. Yousaf

Yascon Center, Chenab Rangers Road, Opposite Kent Housing, Sialkot.

Project: Garrison Academy 204 Bridge Co Gwa Cantt (Multi Purpose Hall Gwa Cantt).

Our Ref. No. CL/CED/ 51 Dated: 28-04-20

Your Ref. No. YAS/UET/07/11 Dated: 06-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 23-04-20 in dry/wet condition

		Ca	astin	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RCC Foundation	9	2	2020	6Diax12	13.2	28.28	43	3410	Non Engraved
2	RCC Foundation	9	2	2020	6Diax12	13	28.28	45	3570	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10088

To: Muhammad Naseer

Dr. M. Yousaf

Λ

Project: Construction of House at 168-H-DHA V, Lahore.

Our Ref. No. CL/CED/ 52 Dated: 28-04-20

Your Ref. No. Nil Dated: 13-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-03-20 Tested on: 23-04-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		14	2	2020	6Diax12	14	28.28	51	4040	Non Engraved
2		14	2	2020	6Diax12	13.8	28.28	53	4200	Non Engraved
3		14	2	2020	6Diax12	13.6	28.28	50	3960	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10063

To: (Ch. Liaqat Ali), Resident Engineer

Dr. Umbreen

G3 Engineering Consultant (Pvt) Ltd.

Project:Consult. Services for Resident Constt. Supervision of Provision of Missing Specialties for Up Gradation of DHQ Hospital to Teaching Hospital Gwa. (Group 1). (Mumty Slab 6th Floor Main Ramp Block).

Our Ref. No. CL/CED/ 53 Dated: 28-04-20

Your Ref. No. G3/205/1157 Dated: 02-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-03-20 Tested on: 22-04-20 in dry/wet condition

Sr. No.	Mark*			Date* eight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:2:4)	15	11	2019	6Diax12	13.4	28.28	43	3410	Non Engraved
2	(1:2:4)	15	11	2019	6Diax12	13.4	28.28	47	3730	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10063

To: (Ch. Liaqat Ali), Resident Engineer

G3 Engineering Consultant (Pvt) Ltd.

Dr. Umbreen

Project:Consult. Services for Resident Constt. Supervision of Provision of Missing Specialties for Up Gradation of DHQ Hospital to Teaching Hospital Gwa. (Group 1). (Mumty Column 6th Floor Main Ramp Block).

Our Ref. No. CL/CED/ 54 Dated: 28-04-20

Your Ref. No. G3/205/1151 Dated: 02-12-19

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-03-20 Tested on: 22-04-20 in dry/wet condition

Ö		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et W	eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:1.5:3)	20	10	2019	6Diax12	13.8	28.28	73	5790	Engraved
2	(1:1.5:3)	20	10	2019	6Diax12	14	28.28	61	4840	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10082

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-Colony, Phase-I, Lahore. Project: Construction of 75-Shadman-I, Lahore. (Strong Ready Mix).

Our Ref. No. CL/CED/ 55 Dated: 28-04-20

Your Ref. No. Nil Dated: 09-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 27-04-20 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(6000 Psi) Column	8	2	2020	6Diax12	14	28.28	83	6580	Non Engraved
2	(6000 Psi) Column	8	2	2020	6Diax12	13.8	28.28	78	6180	Non Engraved
3	(6000 Psi) Column	8	2	2020	6Diax12	14.4	28.28	94	7450	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10082

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-Colony, Phase-I, Lahore. Project: Construction of 75-Shadman-I, Lahore. (Strong Ready Mix).

Our Ref. No. CL/CED/ 56 Dated: 28-04-20

Your Ref. No. Nil Dated: 09-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 27-04-20 in dry/wet condition

		Ca	astir	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(5500 Psi) RCC Wall	8	2	2020	6Diax12	14	28.28	75	5950	Non Engraved
2	(5500 Psi) RCC Wall	8	2	2020	6Diax12	14.2	28.28	88	6970	Non Engraved
3	(5500 Psi) RCC Wall	8	2	2020	6Diax12	14.4	28.28	86	6820	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10082

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-Colony, Phase-I, Lahore.

Project: Construction of 75-Shadman-I, Lahore. (Tetra Engineering (Pvt) Ltd.)

Our Ref. No. CL/CED/ 57 Dated: 28-04-20

Your Ref. No. Nil Dated: 09-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 27-04-20 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(5500 Psi) Lift Wall	2	3	2020	6Diax12	15	28.28	93	7370	Non Engraved
2	(5500 Psi) Lift Wall	2	3	2020	6Diax12	14	28.28	73	5790	Non Engraved
3	(5500 Psi) Lift Wall	2	3	2020	6Diax12	15	28.28	94	7450	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13					_					
14										
15										
16										

 $Results\ can\ also\ be\ seen\ on\ website\ \underline{http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports\&id=6}$

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10082

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-Colony, Phase-I, Lahore.

Project: Construction of 75-Shadman-I, Lahore. (Tetra Engineering (Pvt) Ltd.)

Our Ref. No. CL/CED/ 58 Dated: 28-04-20

Your Ref. No. Nil Dated: 10-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-03-20 Tested on: 27-04-20 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(3000 Psi) Slab & Beam	4	3	2020	6Diax12	14.8	28.28	50	3960	Non Engraved
2	(3000 Psi) Slab & Beam	4	3	2020	6Diax12	13.6	28.28	47	3730	Non Engraved
3	(3000 Psi) Slab & Beam	4	3	2020	6Diax12	14	28.28	50	3960	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10091

o: Yasir Hussain, Assistant Resident Engineer

Dr. M. Yousaf

ES Consultants Pvt. Ltd.

Project: Construction of Additional Class Rooms in Selected Schools of Punjab (Package-2) Govt. Girls Primary School Beroon Daddoki, Tehsil & District Kasur.

Our Ref. No. CL/CED/ 59 Dated: 28-04-20

Your Ref. No. ESC/PMIU/P2/0061 Dated: 13-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-03-20 Tested on: 23-04-20 in dry/wet condition

Sr. No.	Mark*			Date*	Size (in)	Weight (lbs./gms)	Area of X-	Ultimate load	Ultimate Stress	Remarks
S			(gm		, ,	, ,	Section (Sq. in)	(Tons/lbs)	(Psi)	
1		13	2	2020	6x6x6	9	36	112	6970	Engraved
2		13	2	2020	6x6x6	9	36	110	6850	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10042

To: Sub Divisional Officer

Dr. Umbreen

Public Health Engg: Sub Division, Gojra. (Ch. Mushtaq, Govt. Contractor).

Project: Provision of Laying Tuff Tiles, Sewerage and Nallahs in Gojra City District Toba Tek Singh. (Manufactured by Innovative Private Limited, Taxila).

Our Ref. No. CL/CED/ 60 Dated: 28-04-20

Your Ref. No. 141/G Dated: 02-03-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-03-20 Tested on: 22-04-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
S		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Recangular, Grey		7.7x3.8x2.2	2658	29.26	140	10720	
2	Recangular, Grey		7.7x3.8x2.2	2690	29.26	134	10260	
3	Recangular, Grey		7.7x3.8x2.2	2745	29.26	104	7970	
4	Recangular, Grey		7.7x3.8x2.2	2696	29.26	160	12250	
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength