

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9907

To: M. Sohail Anjum (Project Manager)

Dr. Aqsa

P-156 Gulberg II Lahore

Project: Construction of P-156 Gulberg II Lahore.

Our Ref. No. CL/CED/ 9836 Dated: 12-02-20

Your Ref. No. P-156-075 Dated: 06-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-02-20 Tested on: 11-02-20 in dry/wet condition

Sr. No.	Mark*		et V	g Date* Veight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate	Ultimate Stress	Remarks
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	236 (3750 Psi)	10	1	2020	6Diax12	14.8	28.28	60	4760	Non Engraved
2	237 (3750 Psi)	10	1	2020	6Diax12	14.6	28.28	69	5470	Non Engraved
3	238 (3750 Psi)	10	1	2020	6Diax12	14	28.28	65	5150	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9913

To: Naeem Yousaf, Resident Engineer

Dr. Aqsa

NESPAK (Pvt) Ltd.

Project: Construction of DHA Office Complex, DHA Bahawalpur.

Our Ref. No. CL/CED/ 9837 Dated: 12-02-20

Your Ref. No. 4401/DHA/NY/05/22 Dated: 07-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-02-20 Tested on: 11-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RCC Raft of Main Building	11	1	2020	6Diax12	13.2	28.28	58	4600	Non Engraved
2	RCC Raft of Main Building	11	1	2020	6Diax12	13.2	28.28	68	5390	Non Engraved
3	RCC Raft of Main Building	11	1	2020	6Diax12	13.1	28.28	65	5150	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9914

To: Muhammad Azeem (Operation Manager)

Dr. Aqsa

Amer Adnan Associates. 17-E-II, Gulberg III, Lahore.

Project: Hotel Building at 24-A Block E / 2 at Gulberg III, Lahore.

Our Ref. No. CL/CED/ 9838 Dated: 12-02-20

Your Ref. No. AAA/24A/0006 Dated: 07-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-02-20 Tested on: 11-02-20 in dry/wet condition

Sr. No.	Mark*		et V	g Date* Veight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Capping Beam	10	1	2020	6Diax12	13.4	28.28	38	3010	Engraved
2	Capping Beam	10	1	2020	6Diax12	14	28.28	43	3410	Engraved
3	Capping Beam	10	1	2020	6Diax12	14	28.28	47	3730	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9921

To: Muhammad Essa (Chief Financial Officer)

Dr. Aqsa

Markhor Developers (Pvt) Ltd. 68-Shadman-I, Lahore.

Project: Construction of 75-Shad Man-I, Lahore.

Our Ref. No. CL/CED/ 9839 Dated: 12-02-20

Your Ref. No. Nil Dated: 10-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10-02-20 Tested on: 11-02-20 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/\	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Tetra Engg. (4500 Psi)	2	2	2020	6Diax12	14	28.28	62	4920	Engraved
2	Tetra Engg. (4500 Psi)	2	2	2020	6Diax12	14.1	28.28	63	4990	Engraved
3	Tetra Engg. (4500 Psi)	2	2	2020	6Diax12	14	28.28	59	4680	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9921

To: Muhammad Essa (Chief Financial Officer)

Dr. Aqsa

Markhor Developers (Pvt) Ltd. 68-Shadman-I, Lahore.

Project: Construction of 75-Shad Man-I, Lahore.

Our Ref. No. CL/CED/ 9840 Dated: 12-02-20

Your Ref. No. Nil Dated: 10-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10-02-20 Tested on: 11-02-20 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Strong Ready Mix (4500 Psi)	2	2	2020	6Diax12	14.1	28.28	51	4040	Engraved
2	Strong Ready Mix (4500 Psi)	2	2	2020	6Diax12	14	28.28	52	4120	Engraved
3	Strong Ready Mix (4500 Psi)	2	2	2020	6Diax12	14.1	28.28	58	4600	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9924

To: Syed Nabeel Hassan (Resident Engineer)

Dr. Aqsa

CM Div., NESPAK (Pvt.) Ltd. Lahore. (M/s M. Siddique Ch. & Co.)

Project: Construction of Entry Gate of Lahore at Thokar Niaz Baig Multan Road, Lahore

(Central Columns 2'-2" ~ 10'-2").

Our Ref. No. CL/CED/ 9841 Dated: 12-02-20

Your Ref. No. 4047-R/13/SNH/07/AHC/223 Dated: 04-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

11-02-

Specimens received on: 10-02-20 Tested on: 20 in dry/wet condition

		Car	ctina	Date*	Size	Woight	Area of	Ultimate	Ultimate	
<u>o</u> .						Weight	X-			
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1		22	1	2020	6Diax12	13.2	28.28	67	5310	Non Engraved
2		22	1	2020	6Diax12	14	28.28	58	4600	Non Engraved
3		22	1	2020	6Diax12	14	28.28	56	4440	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9924

To: Syed Nabeel Hassan (Resident Engineer)

Dr. Aqsa

CM Div., NESPAK (Pvt.) Ltd. Lahore. (M/s M. Siddique Ch. & Co.) Project: Construction of Entry Gate of Lahore at Thokar Niaz Baig Multan Road, Lahore (Central Columns 0'-0" ~ 2'-2").

Our Ref. No. CL/CED/ 9842 Dated: 12-02-20

Your Ref. No. 4047-R/13/SNH/07/AHC/222 Dated: 04-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10-02-20 Tested on: 11-02-20 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		11	1	2020	6Diax12	14	28.28	37	2940	Non Engraved
2		11	1	2020	6Diax12	13	28.28	40	3170	Non Engraved
3		11	1	2020	6Diax12	13.4	28.28	43	3410	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9924

To: Syed Nabeel Hassan (Resident Engineer)

Dr. Aqsa

CM Div., NESPAK (Pvt.) Ltd. Lahore. (M/s M. Siddique Ch. & Co.)
Project: Construction of Entry Gate of Lahore at Thokar Niaz Baig Multan Road, Lahore (Exit Side Columns 18'-2" ~ 26'-2").

Our Ref. No. CL/CED/ 9843 Dated: 12-02-20

Your Ref. No. 4047-R/13/SNH/07/AHC/224 Dated: 04-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10-02-20 Tested on: 11-02-20 in dry/wet condition

ı		,								
Ġ.		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		26	1	2020	6Diax12	14	28.28	67	5310	Non Engraved
2		26	1	2020	6Diax12	14	28.28	40	3170	Non Engraved
3		26	1	2020	6Diax12	14	28.28	56	4440	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9924

To: Syed Nabeel Hassan (Resident Engineer)

Dr. Aqsa

CM Div., NESPAK (Pvt.) Ltd. Lahore. (M/s M. Siddique Ch. & Co.)

Project: Construction of Entry Gate of Lahore at Thokar Niaz Baig Multan Road, Lahore

(Central Columns 10'-2" ~ 18'-2").

Our Ref. No. CL/CED/ Dated: 12-02-20

Your Ref. No. 4047-R/13/SNH/07/AHC/226 Dated: 04-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10-02-20 Tested on: 11-02-20 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		29	1	2020	6Diax12	13.4	28.28	46	3650	Non Engraved
2		29	1	2020	6Diax12	13.8	28.28	59	4680	Non Engraved
3		29	1	2020	6Diax12	13.2	28.28	44	3490	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9860

To: Sub Divisional Officer

Dr. M. Yousaf

Buildings Sub Division No.6, Lahore

Project: Addition & Improvement Works in Office Buildings in Punjab Civil Secretariat Lahore (S&GAD & Old Health Block)

Our Ref. No. CL/CED/ 9845 Dated: 12-02-20

Your Ref. No. 226/Sd-6th Dated: 20-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 27-01-20 Tested on: 12-02-20 in dry/wet condition

		Са	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:2:4)	21	12	2019	6x6x6	8.5	36	93	5790	Engraved
2	(1:2:4)	21	12	2019	6x6x6	8.5	36	102	6350	Engraved
3	(1:2:4)	21	12	2019	6x6x6	8.4	36	111	6910	Engraved
4	(1:2:4)	21	12	2019	6x6x6	8.6	36	112	6970	Engraved
5	(1:2:4)	21	12	2019	6x6x6	8.9	36	90	5600	Engraved
6	(1:2:4)	21	12	2019	6x6x6	8.4	36	102	6350	Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9903

To: Managing Partner Dr. M. Yousaf

S & S Enterprises, Lahore

Project: Construction of Extension of Shed # 4 for Installation of 18X New Jacquard Looms NCL Weaving

Our Ref. No. CL/CED/ 9846 Dated: 12-02-20

Your Ref. No. NCL-01/0016 Dated: 03-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-02-20 Tested on: 11-02-20 in dry/wet condition

·		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Beam A~Ca/48	29	1	2020	6x6x6	8.6	36	84	5230	Engraved
2	Beam A~Ca/48	29	1	2020	6x6x6	8.4	36	85	5290	Engraved
3	Beam A~Ca/50	30	1	2020	6x6x6	8.6	36	73	4550	Engraved
4	Beam A~Ca/50	30	1	2020	6x6x6	8.6	36	61	3800	Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9876

To: Engr. Roshaan Bin Naghman (Assistant Director Civil)

Dr. M. Yousaf

CAA, AllAP, Lahore

Project: Relocation of Davor / DME to New Localizer Inside Perimeter Fencing at AlIAP, Lahore

Our Ref. No. CL/CED/ 9847 Dated: 12-02-20

Your Ref. No. AIIAP/1656-01/045/LACV/II/57 Dated: 30-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 30-01-20 Tested on: 12-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
Š		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Uniblock Grey		2.3 Thick	3570	37.25	180	10830	
2	Uniblock Grey		2.3 Thick	3470	37.25	180	10830	
3	Uniblock Grey		2.3 Thick	3580	37.25	177	10650	
4	Uniblock Grey		2.3 Thick	3564	37.25	172	10350	
5	Uniblock Grey		2.3 Thick	3585	37.25	152	9140	
6	Uniblock Grey		2.3 Thick	3468	37.25	130	7820	
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9905

To: Pak Construction System

Dr. Aqsa

Chowk Ganga Ram hospital, Lahore Project: Cotton Web Stitching Building

Our Ref. No. CL/CED/ 9848 Dated: 12-02-20

Your Ref. No. Nil Dated: 04-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-02-20 Tested on: 11-02-20 in dry/wet condition

		Ca	astino	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Net V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Grid 3~10/A~G 2nd Floor Roof	24	12	2019.2	6Diax12	13.6	28.28	72	5710	Non Engraved
2	Grid 3~10/A~G 2nd Floor Roof	24	12	2019	6Diax12	13.4	28.28	71	5630	Non Engraved
3	Grid 3~10/A~G 2nd Floor Roof	24	12	2019	6Diax12	13.4	28.28	57	4520	Non Engraved
4	Grid 3~10/A~G 3rd Floor col.	10	1	2020	6Diax12	13.4	28.28	65	5150	Non Engraved
5	Grid 3~10/A~G 3rd Floor col.	10	1	2020	6Diax12	13.4	28.28	50	3960	Non Engraved
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9905

To: Pak Construction System

Dr. Aqsa

Chowk Ganga Ram hospital, Lahore

Project: Cotton Web ETP

Our Ref. No. CL/CED/ 9849 Dated: 12-02-20

Your Ref. No. Nil Dated: 04-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-02-20 Tested on: 11-02-20 in dry/wet condition

		C	asting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Wet V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gr	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Phase I Retaining Wall of ETP	19	12	2019.2	6Diax12	13.6	28.28	45	3570	Non Engraved
2	Phase I Retaining Wall of ETP	19	12	2019	6Diax12	13.8	28.28	35	2780	Non Engraved
3	Phase I Retaining Wall of ETP	19	12	2019	6Diax12	13.4	28.28	48	3810	Non Engraved
4	Phase II Retaining Wall of ETP	30	12	2019	6Diax12	14	28.28	88	6970	Non Engraved
5	Phase II Retaining Wall of ETP	30	12	2019	6Diax12	14	28.28	73	5790	Non Engraved
6	Phase II Retaining Wall of ETP	30	12	2019	6Diax12	14.1	28.28	58	4600	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9908

To: Mohsin Ali (Senior Site Engineer)

Dr. M. Yousaf

AF Builders, Lahore

Project: Building at DHA Shell Filling Station

Our Ref. No. CL/CED/ 9850 Dated: 12-02-20

Your Ref. No. Nil Dated: 04-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-02-20 Tested on: 11-02-20 in dry/wet condition

Ö				g Date*	Size	Weight	Area of X-	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight			(in)	(lbs./gms)	Section	load	Stress	Remarks
			(gr	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	С	15	10	2019.2	6x6x6	8	36	24	1500	Engraved
2	В	3	10	2019	6x6x6	8.9	36	77	4800	Engraved
3	Roof	2	10	2019	6x6x6	8.5	36	73	4550	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9909

To: Altaf Hussain (M.E)

A S Enterprises

Project: Style Textile Raiwind

Our Ref. No. CL/CED/ 9851 Dated: 12-02-20

Your Ref. No. USD/ASE/20 Dated: 04-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-02-20 Tested on: 11-02-20 in dry/wet condition

		Ca	astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	C 20	5	1	2020	6x6x6	8	36	78	4860	Non Engraved
2	C 20	5	1	2020	6x6x6	8.1	36	77	4800	Non Engraved
3	C 20	5	1	2020	6x6x6	8.2	36	83	5170	Non Engraved
4	C 30	5	1	2020	6x6x6	8.1	36	101	6290	Non Engraved
5	C 30	5	1	2020	6x6x6	8.4	36	91	5670	Non Engraved
6	C 30	5	1	2020	6x6x6	8.2	36	88	5480	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9902

o: Furqan Ali Malik (Chief Resident Engineer, Package-1)

Dr.Wasim Abbas

CM Div., NESPAK (Pvt.) Ltd. Lahore

Project: Construction & Rehabilitation of at Grade Works Along Lahore Orange Line Metro Train Corridor Package-1 (Section-I) Pakistan Mint to Shalamar Chowk (Left Side)

Our Ref. No. CL/CED/ 9852 Dated: 12-02-20

Your Ref. No. 4042/13/FAM/Edge-Stone-158 Dated: 03-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-02-20 Tested on: 11-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight (gms)	Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Edge Stone		12x6x7.2	21.2	72	65	2030	Solid Block
2	Edge Stone		12x6x7.2	22	72	55	1720	Solid Block
3								
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength