

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9975

Dr. M. Yousaf

To: Muhammad Essa (Chief Financial Officer)

Markhor Developers (Pvt) Ltd. 68-Shadman-I, Lahore.

Project: Construction of 75-Shadman-I, Lahore.

Our Ref. No. CL/CED/ 9905 Dated: 21-02-20

Your Ref. No. Nil Dated: 19-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 20-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	/Wet Weight (gms)		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
							(Sq. in)	(Tons/lbs)	(Psi)	
1	Strong Ready Mix (6000 Psi) Column	13	2	2020	6Diax12	14	28.28	45	3570	Engraved
2	Strong Ready Mix (6000 Psi) Column	13	2	2020	6Diax12	14.2	28.28	47	3730	Engraved
3	Strong Ready Mix (6000 Psi) Column	13	2	2020	6Diax12	14.4	28.28	50	3960	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9975

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-I, Lahore.

Project: Construction of 75-Shadman-I, Lahore.

Our Ref. No. CL/CED/ 9906 Dated: 21-02-20

Your Ref. No. Nil Dated: 19-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 20-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Strong Ready Mix (4500 Psi) Raft	23	1	2020	6Diax12	14	28.28	69	5470	Engraved
2	Strong Ready Mix (4500 Psi) Raft	23	1	2020	6Diax12	14	28.28	60	4760	Engraved
3	Strong Ready Mix (4500 Psi) Raft	23	1	2020	6Diax12	14	28.28	53	4200	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9975

To: Muhammad Essa (Chief Financial Officer)

Dr. M. Yousaf

Markhor Developers (Pvt) Ltd. 68-Shadman-I, Lahore.

Project: Construction of 75-Shadman-I, Lahore.

Our Ref. No. CL/CED/ 9907 Dated: 21-02-20

Your Ref. No. Nil Dated: 19-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 20-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Tetra Engg. (Pvt) (4500 Psi) Raft	23	1	2020	6Diax12	14.2	28.28	54	4280	Engraved
2	Tetra Engg. (Pvt) (4500 Psi) Raft	23	1	2020	6Diax12	14.4	28.28	58	4600	Engraved
3	Tetra Engg. (Pvt) (4500 Psi) Raft	23	1	2020	6Diax12	14	28.28	55	4360	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9977

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project: Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 9908 Dated: 21-02-20

Your Ref. No. P-156-082 Dated: 20-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 20-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)		ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	344 (3000 Psi)	12	2	2020	6Diax12	13.4	28.28	25	1980	Non Engraved
2	345 (3000 Psi)	12	2	2020	6Diax12	14	28.28	27	2140	Non Engraved
3	346 (3000 Psi)	12	2	2020	6Diax12	14	28.28	28	2220	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9971

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project: Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 9909 Dated: 21-02-20

Your Ref. No. P-156-081 Dated: 19-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-02-20 Tested on: 20-02-20 in dry/wet condition

Ġ.		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
	3,		(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	330 (4500 Psi)	11	2	2020	6Diax12	14	28.28	40	3170	Non Engraved
2	331 (4500 Psi)	11	2	2020	6Diax12	14.2	28.28	40	3170	Non Engraved
3	332 (4500 Psi)	11	2	2020	6Diax12	14	28.28	41	3250	Non Engraved
4	336 (3000 Psi)	11	2	2020	6Diax12	14	28.28	17	1350	Non Engraved
5	337 (3000 Psi)	11	2	2020	6Diax12	14	28.28	31	2460	Non Engraved
6	338 (3000 Psi)	11	2	2020	6Diax12	14.2	28.28	26	2060	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9982

To: Zaroon Construction Services.

Dr. M. Yousaf

Office # 251, Hill View Avenue Adyala Road, Rawalpindi.

Project: "PSO"

Our Ref. No. CL/CED/ 9910 Dated: 21-02-20

Your Ref. No. Nil Dated: 20-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 20-02-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1		12	2	2020	6x6x6	8.6	36	55	3430	Non Engraved
2		12	2	2020	6x6x6	9	36	68	4240	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 9978 Dr.Mazhar saleem

To: Arfan ul Haq (Resident Engineer)

H&TE Sec., Nespak (Pvt.) Ltd. Islamabad. (M/S Banu Mukhtar (Pvt.) Ltd.)

Project: (CPEC), Western Route Hakla (On M1) ~ Yarak (D.I.Khan) Motorway, Package-3

(Tarap to Kot Belian)

Our Ref. No. CL/CED/ 9911 Dated: 21-02-20

Your Ref. No. CPEC/NESPAK/CS/PKG3/1397 Dated: 18-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-02-20 Tested on: 21-02-20 in dry/wet condition

		T	1	T	T	T	T	
		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Kerb Stone		6x6x6	8	36	70	4360	Cut Cube
2	Kerb Stone		6x6x6	8	36	72	4480	Cut Cube
3	Kerb Stone		6x6x6	8	36	75	4670	Cut Cube
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9957 Dr.Mazhar saleem

To: S. Shaukat Hussain (Incharge Civil)
Sui Northern Gas Pipelines Ltd. Lahore

Project: Construction of Road From Main Road to Compressor Station AC-4 UCH Sharif District Bahawalpur

Our Ref. No.

CL/CED/ 9912-1 of 2 Dated: 21-02-20

Your Ref. No. CC/T.Paver/Uch/01 Dated: 14-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14-02-20 Tested on: 21-02-20 in dry/wet condition

Ö		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.8x3.9x2.9	3442	30.42	70	5160	
2	Rectangular Grey		7.8x3.9x2.9	3360	30.42	54	3980	
3	Rectangular Grey		7.8x3.9x2.9	3257	30.42	53	3910	
4	Rectangular Grey		7.8x3.9x2.9	3234	30.42	44	3240	
5	Rectangular Grey		7.8x3.9x2.9	3328	30.42	60	4420	
6	Rectangular Grey		7.8x3.9x2.9	3333	30.42	55	4050	
7	Rectangular Grey		7.8x3.9x2.9	3271	30.42	43	3170	
8	Rectangular Grey		7.8x3.9x2.9	3360	30.42	23	1700	
9	Rectangular Grey		7.8x3.9x2.9	3276	30.42	34	2510	
10	Rectangular Grey		7.8x3.9x2.9	3380	30.42	57	4200	
11								
12								
13								
14					_			
15								
16								

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9957

o: S. Shaukat Hussain (Incharge Civil)

Dr.Mazhar saleem

Sui Northern Gas Pipelines Ltd. Lahore

Project: Construction of Road From Main Road to Compressor Station AC-4 UCH Sharif District Bahawalpu

Our Ref. No. CL/CED/ 9912-2 of 2 Dated: 21-02-20

Your Ref. No. CC/T.Paver/Uch/01 Dated: 14-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14-02-20 Tested on: 21-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet	Size (in)	Weight (lbs./gms)	Area of	Ultimate load	Ultimate Stress	Remarks
Sr.	Wark	Weight	()	(155./9115)	Section			rtemanto
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Kerb Stone		6x6x6	8	36	84	5230	Cut Cube
2	Kerb Stone		6x6x6	8	36	79	4920	Cut Cube
3	Kerb Stone		6x6x6	8	36	97	6040	Cut Cube
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength