



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10009

Dr. M. Yousaf

To: **Engr. Muhammad Javed (Resident Engineer)**
Rizwan Nazir Consulting Engineers (Pvt.) Ltd.
Project: House # 223, Sector-Z, DHA Phase-3, Lahore

Our Ref. No. CL/CED/ 9929 Dated: 26-02-20

Your Ref. No. RNEC/H-233/DHA/20/04 Dated: 25-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		Month	Day	Year						
1		11	2	2020	6Diax12	14.2	28.28	25	1950	Engraved
2		11	2	2020	6Diax12	14	28.28	20	1560	Engraved
3		11	2	2020	6Diax12	14.4	28.28	23	1800	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

9968

Dr. M. Yousaf

To: Rana Sajjad Ali (Resident Engineer)
Al-Imam Enterprises (Pvt.) Ltd. Lahore
Project: Construction of Gold Mall & Apartments (Phase-IV DHA) Lahore

Our Ref. No. CL/CED/ 9930 Dated: 26-02-20

Your Ref. No. Imam/01/GIGA/DHA/LHE/1130 Dated: 17-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight (gms)	Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	C.C Tile		6x6x1	1158	36	97	5940	
2	C.C Tile		6x6x1	1170	36	96	5880	
3	C.C Tile		6x6x1	1172	36	98	6000	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6" dia x 12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

9988
Dr. Aqsa

To: Engr. Rizwan Ahmad (Assistant Resident Engineer)
AR Engineers, Lahore
Project: Construction of Jewel-1 Apartment Plaza at Gulberg-3, Lahore

Our Ref. No. CL/CED/ 9931 Dated: 26-02-20
Your Ref. No. ARST001 Dated: 21-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 21-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		/Wet Weight (gms)								
1	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14.4	28.28	62	4840	Non Engraved
2	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14.4	28.28	68	5300	Non Engraved
3	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14	28.28	73	5690	Non Engraved
4	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14.2	28.28	55	4290	Non Engraved
5	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14.4	28.28	49	3820	Non Engraved
6	F-2 Foundation, Grid 3-12, Line G	24	1	2020	6Diax12	14	28.28	39	3040	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

9990
Dr. Aqsa

To: **Shahid Builders (Pvt.) Ltd.**
Lytton Road, Mozang, Lahore

Project: Construction of Labard Rehabilitation & Vocational Training Centre, Harbanspura, Lahore

Our Ref. No. CL/CED/ 9932 Dated: 26-02-20

Your Ref. No. SBL/2020/5 Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		Month	Day	Year						
1	LGF Slab	18	1	2020	6Diax12	14.2	28.28	57	4450	Non Engraved
2	LGF Slab	18	1	2020	6Diax12	14.1	28.28	52	4060	Non Engraved
3	LGF Slab	18	1	2020	6Diax12	14	28.28	52	4060	Non Engraved
4	LGF Slab	18	1	2020	6Diax12	14.2	28.28	50	3900	Non Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/departments/testing_reports?id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

9993
Dr. Aqsa

To: **Abdullah Hussain (Resident Engineer)**

E&PHE Div., NESPAK (Pvt.) Ltd. Lahore / (M/s HCS-MASTIC JV)

Project: Public Spaces Upgradation of Existing Parks in Sahiwal & Sialkot (Lot-2: Works for Upgradation of Parks in Sialkot)

Our Ref. No. CL/CED/ 9933 Dated: 26-02-20

Your Ref. No. Nespak/SAH/UET/010 Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X-Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		Wet Weight (gms)								
1		27	1	2020	6Diax12	14	28.28	47	3670	Non Engraved
2		27	1	2020	6Diax12	14.1	28.28	59	4600	Non Engraved
3		27	1	2020	6Diax12	13.4	28.28	48	3750	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

9999

Dr. Aqsa

To: Muhammad Irfan (Project Coordinator)
Noor Durrani & Associates, Lahore
Project: Cash & Carry Store and Shopping Complex, at Bosan Road, Multan

Our Ref. No. CL/CED/ 9934 Dated: 26-02-20

Your Ref. No. J/0606/187 Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		Wet Weight (gms)								
1	28 Mpa (18)	22	1	2020	6Diax12	14	28.28	77	6010	Non Engraved
2	28 Mpa (18)	22	1	2020	6Diax12	14	28.28	71	5540	Non Engraved
3	28 Mpa (19)	23	1	2020	6Diax12	14	28.28	76	5930	Non Engraved
4	28 Mpa (19)	23	1	2020	6Diax12	14	28.28	73	5690	Non Engraved
5	35 Mpa (20)	24	1	2020	6Diax12	14	28.28	85	6630	Non Engraved
6	35 Mpa (20)	24	1	2020	6Diax12	14	28.28	75	5850	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/departments/testing_reports?id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6" dia x 12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10000
Dr. Aqsa

To: Site Engineer
N.A Associates, Lahore
Project: Nil

Our Ref. No. CL/CED/ 9935 Dated: 26-02-20
Your Ref. No. Nil Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X-Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		/Wet Weight (gms)								
1	Floor (1:2:4)	21	1	2020	6x6x6	8.2	36	30	1840	Engraved
2	Floor (1:2:4)	21	1	2020	6x6x6	8	36	31	1900	Engraved
3	Floor (1:2:4)	22	1	2020	6x6x6	8	36	33	2020	Engraved
4	Floor (1:2:4)	22	1	2020	6x6x6	8.2	36	25	1540	Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/departments/testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6" dia x 12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10001
Dr. Aqsa

To: Muhammad Essa (Chief Financial Officer)
Markhor Developers (Pvt.) Ltd. Lahore
Project: Construction of 75-Shadman-I, Lahore (Strong Ready Mix)

Our Ref. No. CL/CED/ 9936 Dated: 26-02-20
Your Ref. No. Nil Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		Month	Day	Year						
1	Column (6000 Psi)	17	2	2020	6Diax12	14.2	28.28	46	3590	Engraved
2	Column (6000 Psi)	17	2	2020	6Diax12	14	28.28	44	3430	Engraved
3	Column (6000 Psi)	17	2	2020	6Diax12	14.2	28.28	52	4060	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10001
Dr. Aqsa

To: Muhammad Essa (Chief Financial Officer)
Markhor Developers (Pvt.) Ltd. Lahore
Project: Construction of 75-Shadman-I, Lahore (Strong Ready Mix)

Our Ref. No. CL/CED/ 9937 Dated: 26-02-20
Your Ref. No. Nil Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X-Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		/Wet Weight (gms)								
1	RCC Wall (5500 Psi)	15	2	2020	6Diax12	14	28.28	50	3900	Engraved
2	RCC Wall (5500 Psi)	15	2	2020	6Diax12	14.4	28.28	60	4680	Engraved
3	RCC Wall (5500 Psi)	15	2	2020	6Diax12	14	28.28	46	3590	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10002
Dr. Aqsa

To: Engr. M. Qasim Saeed
Al-Hafeez Group, Lahore
Project: Abdul Kabir Plaza Gulberg-III, Lahore

Our Ref. No. CL/CED/ 9938 Dated: 26-02-20
Your Ref. No. Nil Dated: 24-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		/Wet Weight (gms)								
1	Columns	6	2	2020	6Diax12	13.4	28.28	49	3820	Engraved
2	Columns	6	2	2020	6Diax12	13.8	28.28	47	3670	Engraved
3	Columns	9	2	2020	6Diax12	13.4	28.28	27	2110	Engraved
4	Columns	9	2	2020	6Diax12	13.4	28.28	27	2110	Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/departement?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory
Department of Civil Engineering
University of Engineering and Technology, Lahore
Phone Nos. 042-99029202, 042-99029217

10003
Dr. Aqsa

To: Waqas Zafar (Project Director)
Peach Club, Faisalabad
Project: The Qube, Lahore

Our Ref. No. CL/CED/ 9939 Dated: 26-02-20
Your Ref. No. Nil Dated: 21-02-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-02-20 Tested on: 25-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
		/Wet Weight (gms)								
1	Lift Walls B.1 to Ground Floor	10	2	2020	6Diax12	14	28.28	60	4680	Non Engraved
2	Lift Walls B.1 to Ground Floor	10	2	2020	6Diax12	14	28.28	58	4520	Non Engraved
3	Lift Walls B.1 to Ground Floor	10	2	2020	6Diax12	14	28.28	64	4990	Non Engraved
4	Stairs Flights +Landings	14	2	2020	6Diax12	14	28.28	39	3040	Non Engraved
5	Stairs Flights +Landings	14	2	2020	6Diax12	14	28.28	46	3590	Non Engraved
6	Stairs Flights +Landings	14	2	2020	6Diax12	14	28.28	42	3280	Non Engraved
7	Lift Walls B2 to B1	23	1	2020	6Diax12	14	28.28	47	3670	Non Engraved
8	Lift Walls B2 to B1	23	1	2020	6Diax12	14	28.28	52	4060	Non Engraved
9	Lift Walls B2 to B1	23	1	2020	6Diax12	14.1	28.28	49	3820	Non Engraved
10	B-2 Lift Pit Slab	25	1	2020	6Diax12	14.1	28.28	49	3820	Non Engraved
11	B-2 Lift Pit Slab	25	1	2020	6Diax12	14	28.28	69	5380	Non Engraved
12	B-2 Lift Pit Slab	25	1	2020	6Diax12	14.1	28.28	55	4290	Non Engraved
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory