

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: M. Sohail Anjum (Project Manager) P-156 Gulberg II Lahore

9866 Dr. M. Yousaf

Project: Construction of P-156 Gulberg II Lahore.

Our Ref. No. CL/CED/	9779	Dated:	03-02-20
Your Ref. No.	P-156-067	Dated:	29-01-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

29-01-20 Tested on:

30-01-20 in dry/wet condition

		Ca	astin	ig Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	206 (3750 Psi)	1	1	2020	6Diax12	14.6	28.28	53	4200	Non Engraved
2	207 (3750 Psi)	1	1	2020	6Diax12	14.4	28.28	55	4360	Non Engraved
3	208 (3750 Psi)	1	1	2020	6Diax12	14.8	28.28	40	3170	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

#### To: Sub Divisional Officer

9882 Dr. M. Yousaf

Buildings Sub Division C.M Sectt; Lahore. Project: Construction of 3-Nos Houses in Place of 4-College Road in GOR-1, Lahore.

Our Ref. No. CL/CED/	9780	Dated:	03-02-20
Your Ref. No.	SDO/CMS/1002	Dated:	28-01-20

Tested on:

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

31-01-20

03-02-20 in dry/wet condition

· · · · ·										
Ŀ		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	ſW	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column/Beam/ Slab (1:2:4)	27	1	2020	6x6x6	8	36	20	1250	Engraved
2	Column/Beam/ Slab (1:2:4)	27	1	2020	6x6x6	8	36	20	1250	Engraved
3	Column/Beam/ Slab (1:2:4)	27	1	2020	6x6x6	8	36	15	940	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										
Resu	lts can also be seen on	web	cito		•	•	•			U

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 9852 Dr. M. Yousaf

#### Sub Divisional Officer To: Public Health Engg: Sub Division Daska. Project: Construction of Streets (Drains, PCC) Mohallah Sharif Pur, Habib Pura, Bashir Pura, Nazir Abad Colony and others.

Our Ref. No. CL/CED/	9781	Dated:	03-02-20
Your Ref. No.	18/D	Dated:	23-01-20

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

24-01-20 Tested on: 03-02-20 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Uniblock Grey		2.2 thick	3212	37.25	120	7220	
2	Uniblock Grey		2.2 thick	3250	37.25	109	6560	
3	Uniblock Red		2.2 thick	3450	37.25	104	6260	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

9852 Dr. M. Yousaf

To: Sub Divisional Officer Public Health Engg: Sub Division Daska. Project: Construction of Streets (Drains, PCC) Mohallah Sharif Pur, Habib Pura, Bashir Pura, Nazir Abad Colony and others.

Our Ref. No. CL/CED/	9782	Dated:	03-02-20
Your Ref. No.	21/D	Dated:	23-01-20

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

24-01-20 Tested on:

03-02-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Size (in)	Weight (Ibs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Uniblock Grey		3.0 thick	4396	37.25	57	3430	
2	Uniblock Grey		3.0 thick	4387	37.25	63	3790	
3	Uniblock Red		3.0 thick	4631	37.25	100	6020	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

9852 Dr. M. Yousaf

Public Health Engg: Sub Division Daska. Project: Provision of PCC/ Soling/ Nullah/ Street Scheme at Adalat Garah Bashamula, Muzaffarpura, Dhanay, Phabarainawala, Gujranwala, Ravail Pura, Stabgary, Burj/Butter etc.

Our Ref. No. CL/CED/	9783	Dated:	03-02-20
Your Ref. No.	24/D	Dated:	23-01-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

24-01-20 Tested on:

03-02-20

0 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight (gms)	Size (in)	Weight (lbs./gms)	Area of X-Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Uniblock Grey		2.2 thick	3560	37.25	116	6980	
2	Uniblock Grey		2.2 thick	3439	37.25	107	6440	
3	Uniblock Red		2.2 thick	3456	37.25	131	7880	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16			/					

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6

\* as engraved on the specimens (if any)

\*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)