

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: M. Sohail Anjum, Project Manager

9785 Dr. Aqsa

Multistory Offices. P-156 Gulberg II Lahore.

Project: Construction of P-156 Gulberg II, Lahore.

Our Ref. No. CL/CED/	9679	Dated:	16-01-20
Your Ref. No.	P-156-054	Dated:	10-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-01-20 Tested on:

14-01-20 in dry/wet condition

						1				
		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	Λ	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	209 (3750 Psi)	3	1	2020	6Diax12	14.1	28.28	43	3410	Non Engraved
2	210 (3750 Psi)	3	1	2020	6Diax12	14.2	28.28	50	3960	Non Engraved
3	211 (3750 Psi)	3	1	2020	6Diax12	13.8	28.28	57	4520	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: M. Sohail Anjum, Project Manager

9785 Dr. Aqsa

Multistory Offices. P-156 Gulberg II Lahore.

Project: Construction of P-156 Gulberg II, Lahore.

Our Ref. No. CL/CED/	9680	Dated:	16-01-20
Your Ref. No.	P-156-055	Dated:	10-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

Tested on: 10-01-20

14-01-20 in dry/wet condition

	Casting Date		Date*	Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/et W	eight/	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	177 (3000 Psi)	14	12	2019	6Diax12	14	28.28	43	3410	Non Engraved
2	178 (3000 Psi)	14	12	2019	6Diax12	14.1	28.28	43	3410	Non Engraved
3	179 (3000 Psi)	14	12	2019	6Diax12	13.2	28.28	57	4520	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Shamshad Hussain, Manager Projects

9787 Dr. Aqsa

Noor Durani & Associates. 52-D1, Gulberg III, Lahore.

Project: Gulberg Hotel at 24A-E2, Gulberg III, Lahore.

Our Ref. No. CL/CED/	9681	Dated:	16-01-20
Your Ref. No.	J/0612/011	Dated:	10-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-01-20 Tested on:

14-01-20 in dry/wet condition

		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Ν	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1		3	1	2020	6Diax12	14.2	28.28	40	3170	Engraved
2		3	1	2020	6Diax12	14	28.28	42	3330	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Usman Ali, Project Manager Maypole Lime Light. **Project: Front Building.**

Our Ref. No. CL/CED/	9682	Dated:	16-01-20
Your Ref. No.	MLL-15	Dated:	10-01-20

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-01-20

14-01-20 in dry/wet condition

		Са	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight		Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Columns (5000 Psi)	5	12	2019	6Diax12	14	28.28	67	5310	Non Engraved
2	Columns (5000 Psi)	5	12	2019	6Diax12	14	28.28	76	6020	Non Engraved
3	Columns (5000 Psi)	5	12	2019	6Diax12	14	28.28	81	6420	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

9789 Dr. Aqsa



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: S & S Enterprises.

0

9791 Dr. Aqsa

Project: Construction of Extension of Shed # 4 for Installation of 18 x New Jacquard Looms-NCL Weaving.

Our Ref. No. CL/CED/	9683	Dated:	16-01-20
Your Ref. No.	NCL-1/0012	Dated:	13-01-20

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

13-01-20

14-01-20 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark* /Wet Weight		(in)	(lbs./gms)	X-Section	load	Stress	Remarks		
0)			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Ba-Footing	15	12	2019	6x6x6	9	36	85	5290	Engraved
2	Ba-Footing	15	12	2019	6x6x6	8.6	36	83	5170	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: S & S Enterprises.

Nil

9791 Dr. Aqsa

Project: Construction of Extension of Shed # 4 for Installation of 18 x New Jacquard Looms-NCL Weaving.

Our Ref. No. CL/CED/	9684	Dated:	16-01-20
Your Ref. No.	NCL-1/0013	Dated:	13-01-20

COMPRESSION TEST REPORT

Tested on:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

13-01-20

14-01-20 in dry/wet condition

		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	M	Vet W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
07			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Ca-Footing	16	12	2019	6x6x6	9	36	91	5670	Non Engraved
2	Ca-Footing	16	12	2019	6x6x6	9	36	73	4550	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)