

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: M/s CIMCON Engineers

Faisal Town, Lahore

Project: Providing and Fixing Kerbs Stone at Sunder Industrial Estate, Sundar Raiwind Road, Lahore

Our Ref. No. CL/CED/	262	Dated:	24-06-20
/our Ref. No.	Nil	Dated:	18-06-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

18-06-20 Tested on:

19-06-20 in dry/wet condition

Casting Size Weight Area of Ultimate Ultimate Date* Š /Wet Remarks Mark* (in) (lbs./gms) X-Section load Stress Weight ັດ (Tons/lbs) (gms) (Sq. in) (Psi) 1 Kerb Stone 5.9x5.8x5.5 7.8 34.22 75 4910 Cut Cube 2 3800 Cut Cube Kerb Stone 5.8x5.7x5.5 76 33.06 56 3 4 5 6 7 8 9 10 11 12 13 14 15 16

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

10202 Dr. M. Yousaf



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

> 10203 Dr. M. Yousaf

Amer Adnan Associates, Lahore									
Project: Hotel Building a	t 24-A Block E/	2 at Gulberg III,	Lahore						
Our Ref. No. CL/CED/	263	Dated:	24-06-20						

Your Ref. No.	AAA/24A/0012	Dated:	19-06-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

To: Muhammad Azeem (Operation Manager)

Specimens received on:

19-06-20 Tested on:

19-06-20 in dry/wet condition

								•		
		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/W	'et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		11	6	2020	6Diax12	14	28.28	30	2380	Non Engraved
2		11	6	2020	6Diax12	14	28.28	29	2300	Non Engraved
3		11	6	2020	6Diax12	14.2	28.28	29	2300	Non Engraved
4		20	5	2020	6Diax12	14	28.28	50	3960	Non Engraved
5		20	5	2020	6Diax12	14	28.28	50	3960	Non Engraved
6		20	5	2020	6Diax12	14.2	28.28	53	4200	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Muhammad Essa (Chief Financial Officer) Markhor Developers (Pvt.) Ltd. Lahore

Project: Construction of 75-Shadman-I, Lahore (Tetra Engineering Pvt. Ltd.)

Our Ref. No. CL/CED/	264	Dated:	24-06-20
Your Ref. No.	Nil	Dated:	19-06-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-06-20 Tested on:

22-06-20 in dry/wet condition

Sr. No.	Mark*	Cas /W	sting 'et V	g Date* Veight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column (6000 Psi)	18	5	2020	6Diax12	14	28.28	110	8720	Non Engraved
2	Column (6000 Psi)	18	5	2020	6Diax12	15	28.28	110	8720	Non Engraved
3	Column (6000 Psi)	18	5	2020	6Diax12	15	28.28	124	9830	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

10204 Dr Mazhar Saleem



To:

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10204

Dr.Mazhar Saleem

Markhor Developer Project: Constructi	Markhor Developers (Pvt.) Ltd. Lahore Project: Construction of 75-Shadman-I, Lahore (Tetra Engineering Pvt. Ltd.)										
Our Ref. No. CL/CED/	265	Dated:	24-0	6-20							
Your Ref. No.	Nil	Dated:	19-0	6-20							
	COMPRESS	SION TEST	r REP	ORT							
oncrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers											
Specimens received on:	19-06-20 Tested	d on: 2	22-06-20	in dry/wet condition							

Muhammad Essa (Chief Financial Officer)

1										
		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	ſW	'et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Column (6000 Psi)	21	6	2020	6Diax12	14.2	28.28	69	5470	Non Engraved
2	Column (6000 Psi)	21	6	2020	6Diax12	14	28.28	71	5630	Non Engraved
3	Column (6000 Psi)	21	6	2020	6Diax12	14	28.28	66	5230	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



To: Muhammad Azeem (Operation Manager)

Project: Hotel Building at 24-A Block E/2 at Gulberg III, Lahore

266

AAA/24A/0013

Amer Adnan Associates, Lahore

Our Ref. No. CL/CED/

Your Ref. No.

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

24-06-20

22-06-20

10206

Dr Mazhar Saleem

COMPRESSION TEST REPORT Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers 22-06-20 Tested on: 22-06-20 Specimens received on: in dry/wet condition Casting Date* Size Weight Area of Ultimate Ultimate Š X-Mark* /Wet Weight (in) (lbs./gms) load Stress Remarks Section ັດ (gms) (Tons/lbs) (Sq. in) (Psi) 1 13 6 2020 6Diax12 14 28.28 29 2300 Non Engraved 2 13 6 2020 6Diax12 2460 13.6 28.28 Non Engraved 31 3 13 6 2020 6Diax12 14 28.28 20 1590 Non Engraved 4 5 6 7 8 9 10 11 12 13 14 15 16

Dated:

Dated:

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Assistant Civil Engineer

10156 Dr Mazhar Saleem

PSIC SIE-IV Gujranwala (M/s Abdul Ghafoor Goheer) Project: Construction of Building & Boundary Wall at SIE IV, Gujranwala

Tested on:

Our Ref. No. CL/CED/	267	Dated:	24-06-20
Your Ref. No.	PSIC/SIE-iV-GRW/ByHand	Dated:	01-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-06-20

11-06-20 in dry/wet condition

		0	etina	Data*	Sizo	Woight	Aroa of	Liltimato	Lilitimato	
òr. No.	ο Σ. Mark* Λ		/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gm	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Gymnasium Roof Slab	12	6	2020	6Diax12	13.2	28.28	57	4520	Non Engraved
2	Gymnasium Roof Slab	12	6	2020	6Diax12	13	28.28	81	6420	Non Engraved
3	Gymnasium Quarters Slab	10	11	2020	6Diax12	13	28.28	55	4360	Non Engraved
4	Gymnasium Quarters Slab	10	11	2020	6Diax12	13	28.28	27	2140	Non Engraved
5	Servant Quarter & Generator Room	10	10	2020	6Diax12	13	28.28	49	3890	Non Engraved
6	Servant Quarter & Generator Room	10	10	2020	6Diax12	12.6	28.28	25	1980	Non Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Assistant Civil Engineer

10156 Dr.Mazhar Saleem

PSIC SIE-IV Gujranwala Project: Construction of Building & Boundary Wall at SIE IV, Gujranwala

Our Ref. No. CL/CED/ 268 Dated: 24-06-20

Your Ref. No.	PSIC/SIE-iV-GRW/ByHand	Dated:	01-01-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-06-20 Tested on:

11-06-20 in dry/wet condition

-	[]							
ġ		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.8x3.9x2.3	2659	30.42	110	8100	
2	Rectangular Grey		7.8x3.9x2.3	2669	30.42	53	3910	
3	Rectangular Grey		7.8x3.9x2.3	2598	30.42	77	5670	
4	Rectangular Grey		7.8x3.9x2.3	2648	30.42	100	7370	
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)