

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

153

To: Escorts Advanced Textile Muridke

Engr. Ubaid

Lahore

**Project: Escorts Advanced Textile Muridke Stitching Unit Construction** 

Our Ref. No. CL/CED/ 1212 Dated: 19-11-20

Your Ref. No. Nil Dated: 18-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-11-20 Tested on: 19-11-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Hollow Block		15.5x7.8x8.0	24	68.46	76	2490	
2	Hollow Block		15.5x7.8x8.0	23	68.46	55	1800	
3	Hollow Block		15.5x7.8x8.0	23	68.46	61	2000	
4	Hollow Block		15.5x7.8x8.0	23.4	68.46	73	2390	
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15	3							
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

127

To: Assistant Municipal Officer (Infrastructure)

Dr. Mazhar Saleem

**Municipal Committee,** 

**Bhalwal** 

Project: Rehabilitation / Repair of Road Post Office Road, Bhalwal

Our Ref. No. CL/CED/ 1213 Dated: 19-11-20

Your Ref. No. 353/MC/BHL Dated: 07-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-11-20 Tested on: 16-11-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight	Date* Size /Wet		Area of X- Section	Ultimate load	Ultimate Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Grey		7.8x3.8x3.1	3587	29.64	86	6500	
2	Rectangular Grey		7.8x3.8x3.1	3542	29.64	90	6810	
3	Rectangular Grey		7.8x3.8x3.1	3647	29.64	102	7710	
4	Rectangular Grey		7.8x3.8x3.1	3614	29.64	112	8470	
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

132

Dr. Umbreen

To: Lt. Col. (R) Muhammad Ibrahim (Estate Engineer)

**Board of Management, Sundar Industrial Estate, Lahore** 

Project: Extension of Jamia Masjid in Cash

Our Ref. No. CL/CED/ 1214 Dated: 19-11-20

Your Ref. No. BOM/SIE/BCD/6028 Dated: 12-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-11-20 Tested on: 17-11-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight			Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
S		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1	3000 Psi	16	10	2020	6x6x6	9	36	81	5040	Engraved
2	3000 Psi	16	10	2020	6x6x6	9.4	36	86	5360	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

133

To: Sub Divisional Officer

Dr. Umbreen

Buildings Construction Sub Division No.2, Lahore

Project: Construction of Police Station Lohari Gate, Lahore

Our Ref. No. CL/CED/ 1215 Dated: 19-11-20

Your Ref. No. 2590/2nd Dated: 11-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-11-20 Tested on: 17-11-20 in dry/wet condition

		Ca	etina	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			/eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0)		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	3rd Floor Slab	19	10	2020	6x6x6	9.4	36	114	7100	Engraved
2	3rd Floor Slab	19	10	2020	6x6x6	9.4	36	124	7720	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

135

Dr. Umbreen

To: M. Sohail Anjum (Project Manager)

P-156 Gulberg II, Lahore

Project: Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 1216 Dated: 19-11-20

Your Ref. No. P-156-165 Dated: 13-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-11-20 Tested on: 17-11-20 in dry/wet condition

	Mark*	Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.		M	et W	eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	621 (4500 Psi)	17	10	2020	6Diax12	15	28.28	65	5150	Non Engraved
2	622 (4500 Psi)	17	10	2020	6Diax12	14.6	28.28	69	5470	Non Engraved
3	623 (4500 Psi)	17	10	2020	6Diax12	15	28.28	65	5150	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

128

To: Nawab Ali Engr. Ubaid

**Pakpattan** 

**Project: RCC Slab** 

Our Ref. No. CL/CED/ 1217 Dated: 19-11-20

Your Ref. No. Nil Dated: 12-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-11-20 Tested on: 19-11-20 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/et W	eight /	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1		13	10	2020	6Diax12	13	28.28	41	3250	Non Engraved
2		13	10	2020	6Diax12	14	28.28	34	2700	Non Engraved
3		13	10	2020	6Diax12	14	28.28	48	3810	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

129

Engr. Ubaid

To: Adal Imtiaz (Flight Lieutenant, Assistant Director)

Fazaia Housing Scheme Phase-II Sharif City Road, Lahore

Project: Central Mosque at Fazaia Housing Scheme (Phase-II) Lahore

Our Ref. No. CL/CED/ 1218 Dated: 19-11-20

Your Ref. No. FHSL-II/5811/1/Org(CA-12) Dated: 10-11-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-11-20 Tested on: 19-11-20 in dry/wet condition

		Са	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	///	√et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Strip Footing (Class- B)	28	9	2020	6Diax12	13.4	28.28	69	5470	Engraved
2	Strip Footing (Class- B)	28	9	2020	6Diax12	13.2	28.28	49	3890	Engraved
3	Column (Class-A)	21	10	2020	6Diax12	13.6	28.28	63	4990	Engraved
4	Column (Class-A)	21	10	2020	6Diax12	13.6	28.28	43	3410	Engraved
5	Column (Class-A)	14	10	2020	6Diax12	13.2	28.28	65	5150	Engraved
6	Column (Class-A)	14	10	2020	6Diax12	13	28.28	62	4920	Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

138

To: Muhammad Zain-Ul-Abadeen (Assistant Resident Engineer)

Engr. Ubaid

E&PHE Div., Nespak (Pvt.) Ltd. Lahore

Project: Strom Water Drainage From Haji Camp to River Ravi Via Lakshami Chowk, Mcleod Road, Nabha Road, Chuburji and Sham Nagar, Lahore (Package-II)

Our Ref. No. CL/CED/ 1219 Dated: 19-11-20

Your Ref. No. 3882/11/MZA/01/228 Dated: 14-11-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-11-20 Tested on: 19-11-20 in dry/wet condition

		Ca	asting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	No-169-176 (4000 Psi)	7	11	2020	6Diax12	14.2	28.28	49	3890	Non Engraved
2	No-169-176 (4000 Psi)	7	11	2020	6Diax12	14.2	28.28	59	4680	Non Engraved
3	No-169-176 (4000 Psi)	7	11	2020	6Diax12	14.2	28.28	55	4360	Non Engraved
4	No. 17-24 (4000 Psi)	17	10	2020	6Diax12	14	28.28	61	4840	Non Engraved
5	No. 17-24 (4000 Psi)	17	10	2020	6Diax12	14.2	28.28	51	4040	Non Engraved
6	No. 17-24 (4000 Psi)	17	10	2020	6Diax12	14.2	28.28	51	4040	Non Engraved
7	,									
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing</a> reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength