

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: L.t. Col. (Retd.) Muhammad Ibrahim (Estate Engineer)

Dr.Mazhar Saleem

Sundar Industrial Estate, Lahore

**Project: Repair of Cycle Track in Cash** 

Our Ref. No. CL/CED/ 978 Dated: 16-10-20

Your Ref. No. BOM/SIE/ BCD/5917 Dated: 15-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-10-20 Tested on: 16-10-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet	Size (in)	Weight (lbs./gms)	Area of	Ultimate load	Ultimate Stress	Remarks
S		Weight (gms)		, ,	Section (Sq. in)	(Tons/lbs)	(Psi)	
		(gillo)			(04. 111)	(10110/100)		
1	I-Section Grey		2.3 Thick	3874	40.77	220	12090	
2	I-Section Grey		2.3 Thick	3700	40.77	138	7590	
3	I-Section Grey		2.3 Thick	3888	40.77	152	8360	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

**Director/Dy. Director Concrete Laboratory** 

6

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10662

To: Muhammad Tahir Yaseen

Dr. M. Yousaf

Elco Enterprises, Lahore

Project: Construction of Allied Bank Limited at High Street Branch, Sahiwal (0352), (Columns Pouring Plinth Beams to 1st Floor Level)

Our Ref. No. CL/CED/ 979 Dated: 16-10-20

Your Ref. No. Nil Dated: 09-10-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-10-20 Tested on: 16-10-20 in dry/wet condition

Sr. No.	Mark*		Cast Dat et W	ting :e* /eight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
S			(gm	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	3500 psi	11	9	2020	6Diax12	13	28.28	43	3410	Non Engraved
2	3500 psi	11	9	2020	6Diax12	13	28.28	37	2940	Non Engraved
3	3500 psi	11	9	2020	6Diax12	13.4	28.28	40	3170	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10679

To: Muhammad Tahir Yaseen

Dr. M. Yousaf

Elco Enterprises, Lahore

Project: Construction of Allied Bank Limited at High Street Branch, Sahiwal (0352), (Strong Room Wall)

Our Ref. No. CL/CED/ 980 Dated: 16-10-20

Your Ref. No. Nil Dated: 12-10-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-10-20 Tested on: 16-10-20 in dry/wet condition

Sr. No.	Mark*			g Date* Veight	Size (in)	Weight (lbs./gms)	Area of X-	Ultimate load	Ultimate Stress	Remarks
S.	Wark	/ • •			(111)	(103./91113)	Section			remand
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	3000 psi	14	9	2020	6Diax12	13	28.28	63	4990	Non Engraved
2	3000 psi	14	9	2020	6Diax12	13.2	28.28	43	3410	Non Engraved
3	3000 psi	14	9	2020	6Diax12	13	28.28	37	2940	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10664

To: Project Manager (Orchard Mall)

Dr. M. Yousaf

Troject Manager (Orchard Man)

Q-Links Property Management Pvt. Ltd. Lhr.

Project: Construction of Orchard Mall, Bahria Orchard, Lahore

Our Ref. No. CL/CED/ 981 Dated: 16-10-20

Your Ref. No. QLPM-OM-17 Dated: 07-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-10-20 Tested on: 16-10-20 in dry/wet condition

		Ca	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*		_	eight 'eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Slab (3000 psi)	27	9	2020	6Diax12	14	28.28	29	2300	Non Engraved
2	Slab (3000 psi)	27	9	2020	6Diax12	14	28.28	28	2220	Non Engraved
3	Slab (3000 psi)	27	9	2020	6Diax12	14	28.28	27	2140	Non Engraved
4	SOG (3000 psi)	2	10	2020	6Diax12	14	28.28	34	2700	Non Engraved
5	SOG (3000 psi)	2	10	2020	6Diax12	13.6	28.28	30	2380	Non Engraved
6	Column (5000 Psi)	2	10	2020	6Diax12	14.4	28.28	53	4200	Non Engraved
7	Column (5000 Psi)	2	10	2020	6Diax12	14.6	28.28	62	4920	Non Engraved
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10666

To: Riaz Ahmad Dr. M. Yousaf

Rana Associates, Lahore

Project: Sonica Heights (18-C, Gulberg Lhr)

Our Ref. No. CL/CED/ 982 Dated: 16-10-20

Your Ref. No. Nil Dated: 09-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-10-20 Tested on: 16-10-20 in dry/wet condition

Ġ.		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Columns (4000 psi)	4	9	2020	6Diax12	14.2	28.28	57	4520	Non Engraved
2	Columns (4000 psi)	4	9	2020	6Diax12	14	28.28	79	6260	Non Engraved
3	Slab (3500 psi)	12	9	2020	6Diax12	14.2	28.28	79	6260	Non Engraved
4	Slab (3500 psi)	12	9	2020	6Diax12	15	28.28	73	5790	Non Engraved
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10669

To: Assistant Executive Engineer

Dr. M. Yousaf

KBCMA, CVAS, Narowal

Project: Construction of Boundary Wall/Gate Office 1&2 and Watch Tower at CVAS, Narowal (Along Gate # 2 Boundary Wall)

Our Ref. No. CL/CED/ 983 Dated: 16-10-20

Your Ref. No. AEE/NC/015 Dated: 29-09-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-10-20 Tested on: 16-10-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Footings (1:2:4)	31	8	2020	6Diax12	14	28.28	41	3250	Engraved
2	Footings ( 1 : 2 : 4 )	31	8	2020	6Diax12	14	28.28	43	3410	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing</a> reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10675

To: Muhammad Azeem (Operation Manager)

Dr. M. Yousaf

Amer Adnan Associates, Lahore

Project: Hotel Building at 24-A Block E/2 at Gulberg III, Lahore

Our Ref. No. CL/CED/ Dated: 16-10-20

Your Ref No. AAA/24A/0021 Dated: 12-10-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

12-10-20 Tested on: Specimens received on: 16-10-20 in dry/wet condition

		Ca	asting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	//	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	5000 Psi	4	10	2020	6Diax12	13.6	28.28	40	3170	Non Engraved
2	5000 Psi	4	10	2020	6Diax12	13.8	28.28	43	3410	Non Engraved
3	5000 Psi	4	10	2020	6Diax12	13.6	28.28	62	4920	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10678

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project:Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 985 Dated: 16-10-20

Your Ref. No. P-156-147 Dated: 12-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-10-20 Tested on: 16-10-20 in dry/wet condition

		Ca	asting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	588 (4500 Psi)	3	10	2020	6Diax12	14.8	28.28	68	5390	Non Engraved
2	589 (4500 Psi)	3	10	2020	6Diax12	14.8	28.28	69	5470	Non Engraved
3	590 (4500 Psi)	3	10	2020	6Diax12	14	28.28	69	5470	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10678

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project:Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 986 Dated: 16-10-20

Your Ref. No. P-156-148 Dated: 12-10-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-10-20 Tested on: 16-10-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	552 (3000 Psi)	13	9	2020	6Diax12	14	28.28	43	3410	Non Engraved
2	554 (3000 Psi)	13	9	2020	6Diax12	14.2	28.28	38	3010	Non Engraved
3	555 (3000 Psi)	13	9	2020	6Diax12	14.2	28.28	40	3170	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10698

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project:Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 987 Dated: 16-10-20

Your Ref. No. P-156-149 Dated: 14-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-10-20 Tested on: 16-10-20 in dry/wet condition

		Ca	asting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	N	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	596 (4500 Psi)	7	10	2020	6Diax12	14.4	28.28	58	4600	Non Engraved
2										
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10698

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project:Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 988 Dated: 16-10-20

Your Ref. No. P-156-150 Dated: 14-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-10-20 Tested on: 16-10-20 in dry/wet condition

Ġ.		Ca	asting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/\	Vet V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	600 (3000 Psi)	7	10	2020	6Diax12	14.2	28.28	43	3410	Non Engraved
2	602 (3000 Psi)	7	10	2020	6Diax12	14	28.28	46	3650	Non Engraved
3	604 (3000 Psi)	7	10	2020	6Diax12	14	28.28	39	3090	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10698

To: M. Sohail Anjum (Project Manager)

Dr. M. Yousaf

P-156 Gulberg II, Lahore

Project:Construction of P-156 Gulberg II, Lahore

Our Ref. No. CL/CED/ 989 Dated: 16-10-20

Your Ref. No. P-156-151 Dated: 14-10-20

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-10-20 Tested on: 16-10-20 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	557 (3000 Psi)	17	9	2020	6Diax12	14.6	28.28	61	4840	Non Engraved
2	558 (3000 Psi)	17	9	2020	6Diax12	14	28.28	58	4600	Non Engraved
3	562 (3000 Psi)	17	9	2020	6Diax12	14	28.28	57	4520	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10683

To: Tahir Mehmood Dr. M. Yousaf

Hasnain Builders, Lahore

Project: G.F Slab at Old City SchoolGawal Mandi Lahore (F.Floor Slab)

Our Ref. No. CL/CED/ 990 Dated: 16-10-20

Your Ref. No. Nil Dated: 12-10-20

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-10-20 Tested on: 16-10-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*  /Wet Weight			Size (in)	Weight (lbs./gms)	Area of X-Section	Ultimate	Ultimate	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	3000 Psi	11	9	2020	6Diax12	13.4	28.28	38	3010	Non Engraved
2	3000 Psi	11	9	2020	6Diax12	13.2	28.28	39	3090	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <a href="http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6">http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing\_reports&id=6</a>

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

<sup>\*</sup> as engraved on the specimens (if any)

<sup>\*\*</sup> BS3921 requires average of ten clay brick samples for crushing strength and water absorption

<sup>\*\*\*</sup> BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

<sup>\*\*\*\*</sup> ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength