

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10574

To: Altaf Hussain (GM Engineering)

Dr.Mazhar Saleem

Pak Construction System, Lahore

Project: Construction of Effluent Treatment Plant in Cotton Web Ltd.

Our Ref. No. CL/CED/ 857 Dated: 21-09-20

Your Ref. No. Nil Dated: 16-09-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-09-20 Tested on: 21-09-20 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	ETP R Wall	17	8	2020	6Diax12	13.4	28.28	63	4990	Non Engraved
2	ETP R Wall	17	8	2020	6Diax12	13.4	28.28	57	4520	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

10574

To: Altaf Hussain (GM Engineering)

Dr.Mazhar Saleem

Pak Construction System, Lahore

Project: Construction of Effluent Treatment Plant in Cotton Web Ltd.

Our Ref. No. CL/CED/ 858 Dated: 21-09-20

Your Ref. No. Nil Dated: 16-09-20

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-09-20 Tested on: 21-09-20 in dry/wet condition

Sr. No.	Mark*	Casting Date* /Wet Weight			Size	Weight	Area of	Ultimate	Ultimate	
					(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	ETP Slab	25	8	2020	6Diax12	13	28.28	55	4360	Non Engraved
2	ETP Slab	25	8	2020	6Diax12	13.4	28.28	53	4200	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength